

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau

## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification<sup>6</sup>:C08G 63/692, A61L 17/00, 25/00, 27/00,  
A61K 9/16

A1

(11) International Publication Number:

WO 98/44021

(43) International Publication Date:

8 October 1998 (08.10.98)

(21) International Application Number: PCT/US98/06381

(22) International Filing Date: 2 April 1998 (02.04.98)

(30) Priority Data:

08/832,215

3 April 1997 (03.04.97)

US

(71) Applicants: GUILFORD PHARMACEUTICALS INC.  
[US/US]; 6611 Tributary Street, Baltimore, MD 21224  
(US). JOHNS HOPKINS UNIVERSITY SCHOOL OF  
MEDICINE [US/US]; Suite 72-100, 2024 East Monument,  
Baltimore, MD 21205 (US).(72) Inventors: MAO, Hai-quan; Apartment C8, 334 Stephenson  
Lane, Towson, MD 21204 (US). LEONG, Kam, W.;  
10242 Breconshire Road, Ellicott City, MD 21234 (US).  
DANG, Wenbin; 2320 F Tarleton Lane, Baltimore, MD  
21234 (US). LO, Hungnan; 3702 Lattimore Road, Shaker  
Heights, OH 44122 (US). ZHAO, Zhong; 2320 F Tarleton  
Lane, Baltimore, MD 21234 (US). NOWOTNIK, David,  
P.; 10 Wesley Woods Court, Kingsville, MD 21087 (US).  
ENGLISH, James, P.; 2440 County Road 39, Chelsea, AL  
35043 (US).(74) Agent: NATH, Gary, M.; Nath & Associates, Suite 750, 1835  
K Street, N.W., Washington, DC 20006 (US).(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR,  
BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE,  
GH, GM, GW, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ,  
LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW,  
MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ,  
TM, TR, TT, UA, UG, UZ, VN, YU, ZW, ARIPO patent  
(GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent  
(AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent  
(AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT,  
LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI,  
CM, GA, GN, ML, MR, NE, SN, TD, TG).



Published

With international search report.

(54) Title: BIODEGRADABLE TEREPHTHALATE POLYESTER-POLY(PHOSPHATE) POLYMERS, COMPOSITIONS, ARTICLES,  
AND METHODS FOR MAKING AND USING THE SAME

## (57) Abstract

Biodegradable terephthalate polymers are described comprising the recurring monomeric units shown in formula (I): wherein R is a divalent organic moiety; R' is an aliphatic, aromatic or heterocyclic residue; x is  $\geq 1$ ; and n is 0-5,000, wherein the biodegradable polymer is biocompatible before and upon biodegradation. Processes for preparing the polymers, compositions containing the polymers and biologically active substances, articles useful for implantation or injection into the body fabricated from the compositions, and methods for controllably releasing biologically active substances using the polymers, are also described.



**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

5

10

BIODEGRADABLE TEREPHTHALATE POLYESTER-POLY(PHOSPHATE)  
POLYMERS, COMPOSITIONS, ARTICLES, AND  
METHODS FOR MAKING AND USING THE SAME

BACKGROUND OF THE INVENTION

1. Field of the Invention

The present invention relates to biodegradable  
homopolymer and block copolymer compositions, in particular  
those containing both phosphate and terephthalate ester  
linkages in the polymer backbone, which degrade *in vivo* into  
non-toxic residues. The polymers of the invention are  
particularly useful as implantable medical devices and drug  
delivery systems.

2. Description of the Prior Art

Biocompatible polymeric materials have been used  
extensively in therapeutic drug delivery and medical implant  
device applications. Sometimes, it is also desirable for  
such polymers to be, not only biocompatible, but also  
biodegradable to obviate the need for removing the polymer  
once its therapeutic value has been exhausted.

Conventional methods of drug delivery, such as frequent  
periodic dosing, are not ideal in many cases. For example,  
with highly toxic drugs, frequent conventional dosing can  
result in high initial drug levels at the time of dosing,  
often at near-toxic levels, followed by low drug levels  
between doses that can be below the level of their  
therapeutic value. However, with controlled drug delivery,  
drug levels can be more easily maintained at therapeutic,  
but non-toxic, levels by controlled release in a predictable  
manner over a longer term.

If a biodegradable medical device is intended for use  
as a drug delivery or other controlled-release system, using  
a polymeric carrier is one effective means to deliver the  
therapeutic agent locally and in a controlled fashion, see


Langer et al., "Chemical and Physical Structures of Polymers as Carriers for Controlled Release of Bioactive Agents", *J. Macro. Science, Rev. Macro. Chem. Phys.*, C23:1, 61-126 (1983). As a result, less total drug is required, and toxic side effects can be minimized. Polymers have been used as carriers of therapeutic agents to effect a localized and sustained release. See Leong et al., "Polymeric Controlled Drug Delivery", *Advanced Drug Delivery Reviews*, 1:199-233 (1987); Langer, "New Methods of Drug Delivery", *Science*, 249:1527-33 (1990); and Chien et al., *Novel Drug Delivery Systems* (1982). Such delivery systems offer the potential of enhanced therapeutic efficacy and reduced overall toxicity.

For a non-biodegradable matrix, the steps leading to release of the therapeutic agent are water diffusion into the matrix, dissolution of the therapeutic agent, and diffusion of the therapeutic agent out through the channels of the matrix. As a consequence, the mean residence time of the therapeutic agent existing in the soluble state is longer for a non-biodegradable matrix than for a biodegradable matrix, for which passage through the channels of the matrix, while it may occur, is no longer required. Since many pharmaceuticals have short half-lives, therapeutic agents can decompose or become inactivated within the non-biodegradable matrix before they are released. This issue is particularly significant for many bio-macromolecules and smaller polypeptides, since these molecules are generally hydrolytically unstable and have low permeability through a polymer matrix. In fact, in a non-biodegradable matrix, many bio-macromolecules aggregate and precipitate, blocking the channels necessary for diffusion out of the carrier matrix.

These problems are alleviated by using a biodegradable matrix that, in addition to some diffusion release, also allows controlled release of the therapeutic agent by degradation of the polymer matrix. Examples of classes of synthetic polymers that have been studied as possible

biodegradable materials include polyesters (Pitt et al., "Biodegradable Drug Delivery Systems Based on Aliphatic Polyesters: Application to contraceptives and Narcotic Antagonists", *Controlled Release of Bioactive Materials*, 19-44 (Richard Baker ed., 1980); poly(amino acids) and pseudo-poly(amino acids) (Pulapura et al., "Trends in the Development of Bioresorbable Polymers for Medical Applications", *J. of Biomaterials Appl.*, 6:1, 216-50 (1992); polyurethanes (Bruin et al., "Biodegradable Lysine Diisocyanate-based Poly(Glycolide-co-ε Caprolactone)-Urethane Network in Artificial Skin", *Biomaterials*, 11:4, 291-95 (1990); polyorthoesters (Heller et al., "Release of Norethindrone from Poly(Ortho Esters)", *Polymer Engineering Sci.*, 21:11, 727-31 (1981); and polyanhydrides (Leong et al., "Polyanhydrides for Controlled Release of Bioactive Agents", *Biomaterials* 7:5, 364-71 (1986). Specific examples of biodegradable materials that are used as medical implant materials are polylactide, polyglycolide, polydioxanone, poly(lactide-co-glycolide), poly(glycolide-co-polydioxanone), polyanhydrides, poly(glycolide-co-trimethylene carbonate), and poly(glycolide-co-caprolactone).

Polymers having phosphate linkages, called poly(phosphates), poly(phosphonates) and poly(phosphites), are known. See Penczek et al., *Handbook of Polymer Synthesis*, Chapter 17: "Phosphorus-Containing Polymers", (Hans R. Kricheldorf ed., 1992). The respective structures of these three classes of compounds, each having a different side chain connected to the phosphorus atom, is as follows:




The versatility of these polymers comes from the versatility of the phosphorus atom, which is known for a multiplicity of reactions. Its bonding can involve the 3p orbitals or

various 3s-3p hybrids; spd hybrids are also possible because of the accessible d orbitals. Thus, the physico-chemical properties of the poly(phosphoesters) can be readily changed by varying either the R or R' group. The biodegradability of the polymer is due primarily to the physiologically labile phosphoester bond in the backbone of the polymer. By manipulating the backbone or the sidechain, a wide range of biodegradation rates are attainable.

An additional feature of poly(phosphoesters) is the availability of functional side groups. Because phosphorus can be pentavalent, drug molecules or other biologically active substances can be chemically linked to the polymer. For example, drugs with -O-carboxy groups may be coupled to the phosphorus via an ester bond, which is hydrolyzable. The P-O-C group in the backbone also lowers the glass transition temperature of the polymer and, importantly, confers solubility in common organic solvents, which is desirable for easy characterization and processing.

Login et al., in U.S. Patent Nos. 4,259,222; 4,315,847; and 4,315,969, disclose a poly(phosphate)-polyester polymer having a halogenated terephthalate recurring unit useful in flame retardant materials, but without a phosphorus having a side chain.

Kadiyala et al., *Biomedical Applications of Synthetic Biodegradable Polymers*, Chapter 3: "Poly(phosphoesters): Synthesis, Physicochemical Characterization and Biological Response", 33-57 (Jeffrey O. Hollinger ed., 1995) at page 40 discloses the synthesis of bis(2-hydroxyethyl)terephthalate (BHET) and its subsequent reaction with dimethyl phosphite to form the corresponding poly(phosphite):



A number of other patents disclose flame retardants having a polyester-linked terephthalate recurring unit and


may also have a poly(phosphonate) recurring unit having a -P-R' side chain in which an R' group has replaced the hydrogen atom of a poly(phosphite), but lacking the intervening oxygen of a poly(phosphate). See, for example, Desitter et al., U.S. Patent No. 3,927,231 and Reader, U.S. Patent No. 3,932,566. Starck et al., U.S. Patent No. 597,473 disclose side chains that can be substituted with many kinds of groups including an alkoxy group, but the document as a whole makes it clear that poly(phosphonates), rather than poly(phosphates), are contemplated. (See column 2, lines 28-40.)

Engelhardt et al., U.S. Patent No. 5,530,093 discloses a multitude of textile finishing compositions having a wide variety of polycondensate structures with phosphoester recurring units, including some with terephthalate recurring units, but no guidance is provided to indicate that poly(phosphates), rather than the other two classes of phosphoester polymers, should be selected for making biodegradable materials.

Thus, there remains a need for materials such as the terephthalate polyester-poly(phosphate) polymers of the invention, which are particularly well-suited for making biodegradable materials and other biomedical applications.

## SUMMARY OF THE INVENTION

The biodegradable terephthalate polymers of the invention comprise the recurring monomeric units shown in formula I:



wherein R is a divalent organic moiety;

R' is an aliphatic, aromatic or heterocyclic residue;


x is  $\geq 1$ ; and

n is 0-5,000,


where the biodegradable polymer is sufficiently pure to be

biocompatible and degrades to biocompatible residues upon biodegradation.

In another embodiment, the invention contemplates a process for preparing a biodegradable terephthalate homopolymer comprising the step of polymerizing p moles of a diol compound having formula II:




wherein R is as defined above, with q moles of a phosphoro-dichloridate of formula III:



10

wherein R' is defined as above, and  $p > q$ , to form q moles of a homopolymer of formula IV, shown below:



wherein R, R' and x are as defined above.


15

The invention also contemplates a process for preparing a biodegradable block copolymer comprising the steps of:

- (a) the polymerization step described above; and
- (b) further reacting the homopolymer of formula IV and excess diol of formula II with  $(p - q)$  moles of terephthaloyl chloride having the formula V:

20





to form a block copolymer of formula I.

In another embodiment, the invention comprises a biodegradable terephthalate polymer composition comprising:

- 5           (a) at least one biologically active substance and  
          (b) a polymer having the recurring monomeric units  
              shown in formula I.

10       In yet another embodiment of the invention, an article  
useful for implantation, injection, or otherwise being  
placed totally or partially within the body, comprises the  
biodegradable terephthalate polymer of formula I or the  
above-described polymer composition.

15       In yet another embodiment of the invention, a method is  
provided for the controlled release of a biologically active  
substance comprising the steps of:

- (a) combining the biologically active substance with a  
              biodegradable terephthalate polymer having the  
              recurring monomeric units shown in formula I to  
              form an admixture;  
20       (b) forming the admixture into a shaped, solid  
              article; and  
          (c) implanting or injecting the solid article *in vivo*  
              at a preselected site, such that the solid  
              implanted or injected article is in at least  
25       partial contact with a biological fluid.

#### BRIEF DESCRIPTION OF THE DRAWINGS

Figure 1A shows the DSC curve of P(BHET-EOP/TC, 80/20),  
and Figure 1B shows the DSC curve of P(BHET-EOP/TC, 50/50).

30       Figure 2A shows the <sup>1</sup>H-NMR spectrum, and Figure 2B  
shows the <sup>31</sup>P-NMR spectrum for P(BHET-EOP/TC, 80/20).

Figure 3 shows the FT-IR spectrum for P(BHET-EOP/TC, 80/20).

Figure 4 shows the GPC chromatogram for P(BHET-EOP/TC, 80/20).

5 Figure 5 shows the molecular weights and elemental analyses for P(BHET-EOP/TC, 80/20) and P(BHET-HOP/TC, 90/10).

Figure 6 shows the storage stability of P(BHET-EOP/TC, 80/20) and P(BHET-EOP/TC, 85/15).

10 Figures 7A and 7B show the *in vitro* degradation data for P(BHET-EOP/TC, 80/20) and P(BHET-EOP/TC, 85/15).

Figure 8 shows the change in molecular weight of P(BHDPT-EOP) and P(BHDPT-EOP/TC) poly(phosphoesters) during *in vitro* degradation.

15 Figure 9 shows the *in vivo* degradation of P(BHET-EOP/TC, 80/20) in terms of weight loss.

Figure 10 shows an electron microscopic photograph of P(BHET-EOP/TC, 80/20) microspheres containing FITC-BSA.

20 Figure 11 shows the effect of loading level on the release kinetics of FITC-BSA from microspheres.

Figure 12 shows the lidocaine release from polymer BHDPT-EOP and BHDPT-HOP microspheres.

Figure 13 shows the release of lidocaine from copolymer P(BHDPT-EOP/TC) microspheres.

25 Figure 14 shows the cytotoxicity of P(BHET-EOP/TC, 80/20) microspheres.

Figure 15 shows a toxicity assay plot of relative cell growth (%) vs. concentration of degraded polymer in a tissue-culture well (mg/ml) for four separate polymers.

30 Figure 16 shows a cell toxicity assay plot for two microspheres and their respective monomers.

## DETAILED DESCRIPTION OF THE INVENTION

### Polymers of the Invention


35 As used herein, the term "aliphatic" refers to a linear, branched, or cyclic alkane, alkene, or alkyne. Preferred aliphatic groups in the poly(phosphate) polymer of

the invention are linear or branched alkane having from 1 to 10 carbons, preferably being linear alkane groups of 1 to 7 carbon atoms.

As used herein, the term "aromatic" refers to an unsaturated cyclic carbon compound with  $4n+2$   $\pi$  electrons.

As used herein, the term "heterocyclic" refers to a saturated or unsaturated ring compound having one or more atoms other than carbon in the ring, for example, nitrogen, oxygen or sulfur.

The biodegradable terephthalate polymer of the invention comprises the recurring monomeric units shown in formula I:




wherein R is a divalent organic moiety. R can be any divalent organic moiety so long as it does not interfere with the polymerization, copolymerization, or biodegradation reactions of the polymer. Specifically, R can be an aliphatic group, for example, alkylene, such as ethylene, 1,2-dimethylethylene, n-propylene, isopropylene, 2-methylpropylene, 2,2'-dimethyl-propylene or tert-butylene, tert-pentylene, n-hexylene, n-heptylene and the like; alkenylene, such as ethenylene, propenylene, dodecenylene, and the like; alkynylene, such as propynylene, hexynylene, octadecenynylene, and the like; an aliphatic group substituted with a non-interfering substituent, for example, hydroxy-, halogen- or nitrogen-substituted aliphatic group; or a cycloaliphatic group such as cyclopentylene, 2-methylcyclopentylene, cyclohexylene, cyclohexenylene and the like.

R can also be a divalent aromatic group, such as phenylene, benzylene, naphthalene, phenanthrenylene, and the like, or a divalent aromatic group substituted with a non-interfering substituent. Further, R can be a divalent heterocyclic group, such as pyrrolylene, furanylene,

thiophenylene, alkylene-pyrrolylene-alkylene, pyridylene, pyridinylene, pyrimidinylene and the like, or may be any of these substituted with a non-interfering substituent.

Preferably, however, R is an alkylene group, a  
5 cycloaliphatic group, a phenylene group, or a divalent group having the formula:



wherein X is oxygen, nitrogen, or sulfur, and n is 1 to 3. More preferably, R is an alkylene group having from 1 to 7  
10 carbon atoms and, most preferably, R is an ethylene group, a 2-methyl-propylene group, or a 2,2'-dimethylpropylene group.

R' in the polymer of the invention is an aliphatic, aromatic or heterocyclic residue. When R' is aliphatic, it is preferably alkyl, such as methyl, ethyl, n-propyl,  
15 isopropyl, n-butyl, tert-butyl, -C<sub>8</sub>H<sub>17</sub>, and the like; alkyl substituted with a non-interfering substituent, such as halogen, alkoxy or nitro; or alkyl conjugated to a biologically active substance to form a pendant drug delivery system. When R' is aromatic, it typically contains  
20 from about 5 to about 14 carbon atoms, preferably about 5 to 12 carbon atoms and, optionally, can contain one or more rings that are fused to each other. Examples of particularly suitable aromatic groups include phenyl, naphthyl, anthracenyl, phenanthrenyl and the like.


When R' is heterocyclic, it typically contains from about 5 to 14 ring atoms, preferably from about 5 to 12 ring atoms, and one or more heteroatoms. Examples of suitable heterocyclic groups include furan, thiophene, pyrrole, isopyrrole, 3-isopyrrole, pyrazole, 2-isoimidazole,  
25 1,2,3-triazole, 1,2,4-triazole, oxazole, thiazole, isothiazole, 1,2,3-oxadiazole, 1,2,4-oxadiazole, 1,2,5-oxadiazole, 1,3,4-oxadiazole, 1,2,3,4-oxatriazole, 1,2,3,5-oxatriazole, 1,2,3-dioxazole, 1,2,4-dioxazole,  
30

1,3,2-dioxazole, 1,3,4-dioxazole, 1,2,5-oxatriazole,  
1,3-oxathiole, 1,2-pyran, 1,4-pyran, 1,2-pyrone, 1,4-pyrone,  
1,2-dioxin, 1,3-dioxin, pyridine, N-alkyl pyridinium,  
pyridazine, pyrimidine, pyrazine, 1,3,5-triazine,  
5 1,2,4-triazine, 1,2,3-triazine, 1,2,4-oxazine,  
1,3,2-oxazine, 1,3,5-oxazine, 1,4-oxazine, o-isoxazine,  
p-isoxazine, 1,2,5-oxathiazine, 1,2,6-oxathiazine,  
1,4,2-oxadiazine, 1,3,5,2-oxadiazine, azepine, oxepin,  
thiepin, 1,2,4-diazepine, indene, isoindene, benzofuran,  
10 isobenzofuran, thionaphthene, isothionaphthene, indole,  
indolenine, 2-isobenzazole, 1,4-pyrindine, pyrand[3,4-b]-  
pyrrole, isoindazole, indoxazine, benzoxazole, anthranil,  
1,2-benzopyran, 1,2-benzopyrone, 1,4-benzopyrone,  
2,1-benzopyrone, 2,3-benzopyrone, quinoline, isoquinoline,  
15 12,-benzodiazine, 1,3-benzodiazine, naphthyridine,  
pyrido[3,4-b]-pyridine, pyrido[3,2-b]-pyridine, pyrido[4,3-  
b]pyridine, 1,3,2-benzoxazine, 1,4,2-benzoxazine,  
2,3,1-benzoxazine, 3,1,4-benzoxazine, 1,2-benzisoxazine,  
1,4-benzisoxazine, carbazole, xanthrene, acridine, purine,  
20 and the like. Preferably, when R' is heterocyclic, it is  
selected from the group consisting of furan, pyridine,  
N-alkylpyridine, 1,2,3- and 1,2,4-triazoles, indene,  
anthracene and purine.

In a particularly preferred embodiment, R' is an alkyl  
25 group or a phenyl group and, even more preferably, an alkyl  
group having from 1 to 7 carbon atoms. Most preferably, R'  
is an ethyl group.

The value of x can vary greatly depending on the  
desired solubility of the polymer, the desired Tg, the  
30 desired stability of the polymer, the desired stiffness of  
the final polymers, and the biodegradability and the release  
characteristics desired in the polymer. However, x  
generally is  $\geq 1$  and, typically, varies between about 1 and  
40. Preferably, x is from about 1 to about 30, more  
35 preferably, from about 1 to about 20 and, most preferably,  
from about 2 to about 20.

The most common way of controlling the value of x is to vary the feed ratio of the "x" portion relative to the other monomer. For example, in the case of making the polymer:



5 widely varying feed ratios of the ethyl phosphoro-  
dichloridate "x" reactant ("EOP") can be used with the  
terephthaloyl chloride reactant ("TC"). Feed ratios of EOP  
to TC can easily vary from 99:1 to 1:99, for example, 95:5,  
90:10, 85:15, 80:20, 75:25, 70:30, 65:35, 60:40, 55:45,  
10 50:50, 45:55, 20:80, 15:85, and the like. Preferably, the  
EOP/TC feed ratio varies from about 90:10 to about 50:50;  
even more preferably, from about 85:15 to about 50:50; and,  
most preferably from about 80:20 to about 50:50.

The number n can vary greatly depending on the  
15 biodegradability and the release characteristics desired in  
the polymer, but typically varies between about 0 to 5,000,  
preferably between about 2 and 500. More preferably, n is  
from about 5 to about 300 and, most preferably, from about 5  
to about 200.

20 Biodegradable polymers differ from non-biodegradable  
polymers in that they can be degraded during in vivo  
therapy. This generally involves breaking down the polymer  
into its monomeric subunits. In principle, the ultimate  
hydrolytic breakdown products of a poly(phosphate) are  
25 phosphate, alcohol, and diol, all of which are potentially  
non-toxic. The intermediate oligomeric products of the  
hydrolysis may have different properties, but the toxicology  
of a biodegradable polymer intended for implantation or  
injection, even one synthesized from apparently innocuous  
30 monomeric structures, is typically determined after one or  
more in vitro toxicity analyses.

The biodegradable polymer of the invention is  
preferably sufficiently pure to be biocompatible itself and

remains biocompatible upon biodegradation. By  
 "biocompatible" is meant that the biodegradation products or  
 the polymer are non-toxic and result in only minimal tissue  
 irritation when implanted or injected into vasculated  
 5 tissue.


The polymer of the invention is preferably soluble in  
 one or more common organic solvents for ease of fabrication  
 and processing. Common organic solvents include such  
 solvents as chloroform, dichloromethane, acetone, ethyl  
 10 acetate, DMAC, N-methyl pyrrolidone, dimethylformamide, and  
 dimethylsulfoxide. The polymer is preferably soluble in at  
 least one of the above solvents.

The glass transition temperature (T<sub>g</sub>) of the polymer of  
 the invention can vary widely depending upon the degree of  
 15 branching of the diols used to prepare the polymer, the  
 relative proportion of phosphorous-containing monomer used  
 to make the polymer, and the like. However, preferably, the  
 T<sub>g</sub> is within the range of from about -10°C to about 80°C  
 and, even more preferably, between about 0 and 50°C.

20

#### Synthesis of Polyester-Poly(phosphate) Polymers

The most common general reaction in preparing  
 poly(phosphates) is a dehydrochlorination between a  
 phosphorodichloridate and a diol according to the following  
 25 equation:



A Friedel-Crafts reaction can also be used to  
 synthesize poly(phosphates). Polymerization typically is  
 effected by reacting either bis(chloromethyl) compounds with  
 30 aromatic hydrocarbons or chloromethylated diphenyl ether  
 with triaryl phosphates. Poly(phosphates) can also be  
 obtained by bulk condensation between phosphorus

diimidazolides and aromatic diols, such as resorcinol and quinoline, usually under nitrogen or some other inert gas.

5 An advantage of bulk polycondensation is that it avoids the use of solvents and large amounts of other additives, thus making purification more straightforward. It can also provide polymers of reasonably high molecular weight. Somewhat rigorous conditions, however, are often required and can lead to chain acidolysis (or hydrolysis if water is present). Unwanted, thermally-induced side reactions, such as cross-linking reactions, can also occur if the polymer backbone is susceptible to hydrogen atom abstraction or oxidation with subsequent macroradical recombination. To minimize these side reactions, the polymerization is preferably carried out in solution.

15 Solution polycondensation requires that both the diol and the phosphorus component be soluble in a common solvent. Typically, a chlorinated organic solvent is used, such as chloroform, dichloromethane, or dichloroethane. The solution polymerization is preferably run in the presence of equimolar amounts of the reactants and a stoichiometric amount of an acid acceptor, usually a tertiary amine such as pyridine or triethylamine. The product is then typically isolated from the solution by precipitation with a non-solvent and purified to remove the hydrochloride salt by conventional techniques known to those of ordinary skill in the art, such as by washing with an aqueous acidic solution, e.g., dilute HCl.


20 Reaction times tend to be longer with solution polymerization than with bulk polymerization. However, because overall milder reaction conditions can be used, side reactions are minimized, and more sensitive functional groups can be incorporated into the polymer. The disadvantages of solution polymerization are that the attainment of high molecular weights, such as a Mw greater than 20,000, is less likely.

35 Interfacial polycondensation can be used when high molecular weight polymers are desired at high reaction




rates. Mild conditions minimize side reactions. Also the dependence of high molecular weight on stoichiometric equivalence between diol and dichloridate inherent in solution methods is removed. However, hydrolysis of the acid chloride may occur in the alkaline aqueous phase. Sensitive dichloridates that have some solubility in water are generally subject to hydrolysis rather than polymerization. Phase transfer catalysts, such as crown ethers or tertiary ammonium chloride, can be used to bring the ionized diol to the interface to facilitate the polycondensation reaction. The yield and molecular weight of the resulting polymer after interfacial polycondensation are affected by reaction time, molar ratio of the monomers, volume ratio of the immiscible solvents, the type of acid acceptor, and the type and concentration of the phase transfer catalyst.


In a preferred embodiment of the invention, the process of making a biodegradable terephthalate homopolymer of formula I comprises the step of polymerizing p moles of a diol compound having formula II:



wherein R is as defined above, with q moles of a phosphorodichloridate of formula III:




wherein R' is defined as above, and  $p > q$ , to form q moles of a homopolymer of formula IV, shown below:



wherein R, R' and x are as defined above. The homopolymer so formed can be isolated, purified and used as is.

Alternatively, the homopolymer, isolated or not, can be used to prepare a block copolymer of the invention by:

- (a) polymerizing as described above; and
- (b) further reacting the homopolymer of formula IV and excess diol of formula II with (p - q) moles of terephthaloyl chloride having the formula V:



to form the polymer of formula I.

The function of the polymerization reaction of step (a) is to phosphorylate the di-ester starting material and then to polymerize it to form the homopolymer. The polymerization step (a) can take place at widely varying temperatures, depending upon the solvent used, the molecular weight desired, the solubility desired, and the susceptibility of the reactants to form side reactions. Preferably, however, the polymerization step (a) takes place at a temperature from about -40 to about +160°C for solution polymerization, preferably from about 0 to 65°C; in bulk, temperatures in the range of about +150°C are generally used.

The time required for the polymerization step (a) also can vary widely, depending on the type of polymerization being used and the molecular weight desired. Preferably,

however, the polymerization step (a) takes place during a time between about 30 minutes and 24 hours.

While the polymerization step (a) may be in bulk, in solution, by interfacial polycondensation, or any other convenient method of polymerization, preferably, the polymerization step (a) is a solution polymerization reaction. Particularly when solution polymerization reaction is used, an acid acceptor is advantageously present during the polymerization step (a). A particularly suitable class of acid acceptor comprises tertiary amines, such as pyridine, trimethylamine, triethylamine, substituted anilines and substituted aminopyridines. The most preferred acid acceptor is the substituted aminopyridine 4-dimethylaminopyridine ("DMAP").

The addition sequence for the polymerization step (a) can vary significantly depending upon the relative reactivities of the diol of formula II, the phosphorodichloridate of formula III, and the homopolymer of formula IV; the purity of these reactants; the temperature at which the polymerization reaction is performed; the degree of agitation used in the polymerization reaction; and the like. Preferably, however, the diol of formula II is combined with a solvent and an acid acceptor, and then the phosphorodichloridate is added slowly. For example, a solution of the phosphorodichloridate in a solvent may be trickled in or added dropwise to the chilled reaction mixture of diol, solvent and acid acceptor, to control the rate of the polymerization reaction.

The purpose of the copolymerization of step (b) is to form a block copolymer comprising (i) the phosphorylated homopolymer chains produced as a result of polymerization step (a) and (ii) interconnecting polyester units. The result is a block copolymer having a microcrystalline structure particularly well-suited to use as a controlled release medium.

The copolymerization step (b) of the invention usually takes place at a slightly higher temperature than the

temperature of the polymerization step (a), but also may vary widely, depending upon the type of copolymerization reaction used, the presence of one or more catalysts, the molecular weight desired, the solubility desired, and the susceptibility of the reactants to undesirable side reaction. However, when the copolymerization step (b) is carried out as a solution polymerization reaction, it typically takes place at a temperature between about -40 and 100°C. Typical solvents include methylene chloride, chloroform, or any of a wide variety of inert organic solvents.

The time required for the copolymerization of step (b) can also vary widely, depending on the molecular weight of the material desired and, in general, the need to use more or less rigorous conditions for the reaction to proceed to the desired degree of completion. Typically, however, the copolymerization step (b) takes place during a time of about 30 minutes to 24 hours.

The addition sequence for the copolymerization step (b) can vary significantly depending upon the relative reactivities of the homopolymer of formula IV and the terephthaloyl chloride of formula V; the purity of these reactants; the temperature at which the copolymerization reaction is performed; the degree of agitation used in the copolymerization reaction; and the like. Preferably, however, the terephthaloyl chloride of formula V is added slowly to the reaction mixture, rather than vice versa. For example, a solution of the terephthaloyl chloride in a solvent may be trickled in or added dropwise to the chilled or room temperature reaction, to control the rate of the copolymerization reaction.

The polymer of formula I, whether a homopolymer (where y is 0) or a block copolymer (where Y is greater than 0), is isolated from the reaction mixture by conventional techniques, such as by precipitating out, extraction with an immiscible solvent, evaporation, filtration, crystallization and the like. Typically, however, the polymer of formula I

is both isolated and purified by quenching a solution of said polymer with a non-solvent or a partial solvent, such as diethyl ether or petroleum ether.

When the polymer of the invention is synthesized by a two-step solution polycondensation to produce a block copolymer, the addition sequence of the reactive chlorides and the reaction temperatures in each step are preferably optimized to obtain the combination of molecular weight desired with good solubility in common organic solvents. Preferably, the additive sequence comprises dissolving the bis-terephthalate starting material with an acid acceptor in a solvent in which both are soluble, chilling the solution with stirring, slowly adding an equal molar amount of the phosphorodichloridate (dissolved in the same solvent) to the solution, allowing the reaction to proceed at room temperature for a period of time, slowly adding an appropriate amount of terephthaloyl chloride, which is also dissolved in the same solvent, and increasing the temperature to about 50°C before refluxing overnight.

#### Biodegradability and Release Characteristics

The polymer of formula I is usually characterized by a release rate of the biologically active substance *in vivo* that is controlled, at least in part, as a function of hydrolysis of the phosphoester bond of the polymer during biodegradation. Additionally, the biologically active substance to be released may be conjugated to the phosphorus side chain R' to form a pendant drug delivery system.

Further, the structure of the side chain can influence the release behavior of the polymer. For example, it is expected that conversion of the phosphorous side chain to a more lipophilic, more hydrophobic or bulky group would slow down the degradation process. Thus, for example, release is usually faster from polymer compositions with a small aliphatic group side chain than with a bulky aromatic side chain.

The lifetime of a biodegradable polymer *in vivo* also depends upon its molecular weight, crystallinity, biostability, and the degree of cross-linking. In general, the greater the molecular weight, the higher the degree of crystallinity, and the greater the biostability, the slower biodegradation will be. Accordingly, degradation times can vary widely, preferably from less than a day to several months.

#### 10 Polymer Compositions

The polymer of formula I can be used either alone or as a composition containing, in addition, a biologically active substance to form a variety of useful biodegradable materials. For example, the polymer of formula I can be used to produce a biosorbable suture, an orthopedic appliance or bone cement for repairing injuries to bone or connective tissue, a laminate for degradable or non-degradable fabrics, or a coating for an implantable device, even without the presence of a biologically active substance.

Preferably, however, the biodegradable terephthalate polymer composition comprises both:

- (a) at least one biologically active substance and
- (b) the polymer having the recurring monomeric units shown in formula I where R, R', and x and n are as defined above.

The biologically active substance of the invention can vary widely with the purpose for the composition. The active substance(s) may be described as a single entity or a combination of entities. The delivery system is designed to be used with biologically active substances having high water-solubility as well as with those having low water-solubility to produce a delivery system that has controlled release rates. The term "biologically active substance" includes without limitation, medicaments; vitamins; mineral supplements; substances used for the treatment, prevention, diagnosis, cure or mitigation of disease or illness; or

substances which affect the structure or function of the body; or pro-drugs, which become biologically active or more active after they have been placed in a predetermined physiological environment.

5           Non-limiting examples of broad categories of useful biologically active substances include the following therapeutic categories: anabolic agents, antacids, anti-asthmatic agents, anti-cholesterolemic and anti-lipid agents, anti-coagulants, anti-convulsants, anti-diarrheals, 10 anti-emetics, anti-infective agents, anti-inflammatory agents, anti-manic agents, anti-nauseants, anti-neoplastic agents, anti-obesity agents, anti-pyretic and analgesic agents, anti-spasmodic agents, anti-thrombotic agents, anti-uricemic agents, anti-anginal agents, antihistamines, anti-15 tussives, appetite suppressants, biologicals, cerebral dilators, coronary dilators, decongestants, diuretics, diagnostic agents, erythropoietic agents, expectorants, gastrointestinal sedatives, hyperglycemic agents, hypnotics, hypoglycemic agents, ion exchange resins, laxatives, mineral 20 supplements, mucolytic agents, neuromuscular drugs, peripheral vasodilators, psychotropics, sedatives, stimulants, thyroid and anti-thyroid agents, uterine relaxants, vitamins, and prodrugs.

          More specifically, non-limiting examples of useful 25 biologically active substances include the following therapeutic categories: analgesics, such as nonsteroidal anti-inflammatory drugs, opiate agonists and salicylates; antihistamines, such as H<sub>1</sub>-blockers and H<sub>2</sub>-blockers; anti-30 infective agents, such as anthelmintics, antianaerobics, antibiotics, aminoglycoside antibiotics, antifungal antibiotics, cephalosporin antibiotics, macrolide antibiotics, miscellaneous  $\beta$ -lactam antibiotics, penicillin antibiotics, quinolone antibiotics, sulfonamide antibiotics, tetracycline antibiotics, antimycobacterials, 35 antituberculosis antimycobacterials, antiprotozoals, antimalarial antiprotozoals, antiviral agents, anti-retroviral agents, scabicides, and urinary anti-infectives;

antineoplastic agents, such as alkylating agents, nitrogen  
mustard alkylating agents, nitrosourea alkylating agents,  
antimetabolites, purine analog antimetabolites, pyrimidine  
analog antimetabolites, hormonal antineoplastics, natural  
5 antineoplastics, antibiotic natural antineoplastics, and  
vinca alkaloid natural antineoplastics; autonomic agents,  
such as anticholinergics, antimuscarinic anticholinergics,  
ergot alkaloids, parasympathomimetics, cholinergic agonist  
parasympathomimetics, cholinesterase inhibitor para-  
10 sympathomimetics, sympatholytics,  $\alpha$ -blocker sympatholytics,  
 $\beta$ -blocker sympatholytics, sympathomimetics, and adrenergic  
agonist sympathomimetics; cardiovascular agents, such as  
antianginals,  $\beta$ -blocker antianginals, calcium-channel  
blocker antianginals, nitrate antianginals, antiarrhythmics,  
15 cardiac glycoside antiarrhythmics, class I antiarrhythmics,  
class II antiarrhythmics, class III antiarrhythmics, class  
IV antiarrhythmics, antihypertensive agents,  $\alpha$ -blocker  
antihypertensives, angiotensin-converting enzyme inhibitor  
(ACE inhibitor) antihypertensives,  $\beta$ -blocker antihyper-  
20 tensives, calcium-channel blocker antihypertensives,  
central-acting adrenergic antihypertensives, diuretic  
antihypertensive agents, peripheral vasodilator anti-  
hypertensives, antilipemics, bile acid sequestrant  
antilipemics, HMG-CoA reductase inhibitor antilipemics,  
25 inotropes, cardiac glycoside inotropes, and thrombolytic  
agents; dermatological agents, such as antihistamines, anti-  
inflammatory agents, corticosteroid anti-inflammatory  
agents, antipruritics/local anesthetics, topical anti-  
infectives, antifungal topical anti-infectives, antiviral  
30 topical anti-infectives, and topical antineoplastics;  
electrolytic and renal agents, such as acidifying agents,  
alkalinizing agents, diuretics, carbonic anhydrase inhibitor  
diuretics, loop diuretics, osmotic diuretics, potassium-  
sparing diuretics, thiazide diuretics, electrolyte  
35 replacements, and uricosuric agents; enzymes, such as  
pancreatic enzymes and thrombolytic enzymes;  
gastrointestinal agents, such as antidiarrheals,



antiemetics, gastrointestinal anti-inflammatory agents, salicylate gastrointestinal anti-inflammatory agents, antacid anti-ulcer agents, gastric acid-pump inhibitor anti-ulcer agents, gastric mucosal anti-ulcer agents, H<sub>2</sub>-blocker anti-ulcer agents, cholelitholytic agents, digestants, 5 emetics, laxatives and stool softeners, and prokinetic agents; general anesthetics, such as inhalation anesthetics, halogenated inhalation anesthetics, intravenous anesthetics, barbiturate intravenous anesthetics, benzodiazepine intravenous anesthetics, and opiate agonist intravenous 10 anesthetics; hematological agents, such as antianemia agents, hematopoietic antianemia agents, coagulation agents, anticoagulants, hemostatic coagulation agents, platelet inhibitor coagulation agents, thrombolytic enzyme coagulation agents, and plasma volume expanders; hormones 15 and hormone modifiers, such as abortifacients, adrenal agents, corticosteroid adrenal agents, androgens, anti-androgens, antidiabetic agents, sulfonylurea antidiabetic agents, antihypoglycemic agents, oral contraceptives, 20 progestin contraceptives, estrogens, fertility agents, oxytocics, parathyroid agents, pituitary hormones, progestins, antithyroid agents, thyroid hormones, and tocolytics; immunobiologic agents, such as immunoglobulins, immunosuppressives, toxoids, and vaccines; local 25 anesthetics, such as amide local anesthetics and ester local anesthetics; musculoskeletal agents, such as anti-gout anti-inflammatory agents, corticosteroid anti-inflammatory agents, gold compound anti-inflammatory agents, immuno-suppressive anti-inflammatory agents, nonsteroidal anti-inflammatory drugs (NSAIDs), salicylate anti-inflammatory 30 agents, skeletal muscle relaxants, neuromuscular blocker skeletal muscle relaxants, and reverse neuromuscular blocker skeletal muscle relaxants; neurological agents, such as anticonvulsants, barbiturate anticonvulsants, benzodiazepine anticonvulsants, anti-migraine agents, anti-parkinsonian 35 agents, anti-vertigo agents, opiate agonists, and opiate antagonists; ophthalmic agents, such as anti-glaucoma

agents,  $\beta$ -blocker anti-glaucoma agents, miotic anti-glaucoma agents, mydriatics, adrenergic agonist mydriatics, antimuscarinic mydriatics, ophthalmic anesthetics, ophthalmic anti-infectives, ophthalmic aminoglycoside anti-infectives, ophthalmic macrolide anti-infectives, ophthalmic quinolone anti-infectives, ophthalmic sulfonamide anti-infectives, ophthalmic tetracycline anti-infectives, ophthalmic anti-inflammatory agents, ophthalmic corticosteroid anti-inflammatory agents, and ophthalmic nonsteroidal anti-inflammatory drugs (NSAIDs); psychotropic agents, such as antidepressants, heterocyclic antidepressants, monoamine oxidase inhibitors (MAOIs), selective serotonin re-uptake inhibitors (SSRIs), tricyclic antidepressants, antimanics, antipsychotics, phenothiazine antipsychotics, anxiolytics, sedatives, and hypnotics, barbiturate sedatives and hypnotics, benzodiazepine anxiolytics, sedatives, and hypnotics, and psychostimulants; respiratory agents, such as antitussives, bronchodilators, adrenergic agonist bronchodilators, antimuscarinic bronchodilators, expectorants, mucolytic agents, respiratory anti-inflammatory agents, and respiratory corticosteroid anti-inflammatory agents; toxicology agents, such as antidotes, heavy metal antagonists/chelating agents, substance abuse agents, deterrent substance abuse agents, and withdrawal substance abuse agents; minerals; and vitamins, such as vitamin A, vitamin B, vitamin C, vitamin D, vitamin E, and vitamin K.

Preferred classes of useful biologically active substances from the above categories include: (1) nonsteroidal anti-inflammatory drugs (NSAIDs) analgesics, such as diclofenac, ibuprofen, ketoprofen, and naproxen; (2) opiate agonist analgesics, such as codeine, fentanyl, hydromorphone, and morphine; (3) salicylate analgesics, such as aspirin (ASA) (enteric coated ASA); (4)  $H_1$ -blocker antihistamines, such as clemastine and terfenadine; (5)  $H_2$ -blocker antihistamines, such as cimetidine, famotidine, nizatidine, and ranitidine; (6) anti-infective agents, such as

mupirocin; (7) antianaerobic anti-infectives, such as chloramphenicol and clindamycin; (8) antifungal antibiotic anti-infectives, such as amphotericin b, clotrimazole, fluconazole, and ketoconazole; (9) macrolide antibiotic anti-infectives, such as azithromycin and erythromycin; (10) miscellaneous  $\beta$ -lactam antibiotic anti-infectives, such as aztreonam and imipenem; (11) penicillin antibiotic anti-infectives, such as nafcillin, oxacillin, penicillin G, and penicillin V; (12) quinolone antibiotic anti-infectives, such as ciprofloxacin and norfloxacin; (13) tetracycline antibiotic anti-infectives, such as doxycycline, minocycline, and tetracycline; (14) antituberculosis antimycobacterial anti-infectives such as isoniazid (INH), and rifampin; (15) antiprotozoal anti-infectives, such as atovaquone and dapsone; (16) antimalarial antiprotozoal anti-infectives, such as chloroquine and pyrimethamine; (17) anti-retroviral anti-infectives, such as ritonavir and zidovudine; (18) antiviral anti-infective agents, such as acyclovir, ganciclovir, interferon alfa, and rimantadine; (19) alkylating antineoplastic agents, such as carboplatin and cisplatin; (20) nitrosourea alkylating antineoplastic agents, such as carmustine (BCNU); (21) antimetabolite antineoplastic agents, such as methotrexate; (22) pyrimidine analog antimetabolite antineoplastic agents, such as fluorouracil (5-FU) and gemcitabine; (23) hormonal antineoplastics, such as goserelin, leuprolide, and tamoxifen; (24) natural antineoplastics, such as aldesleukin, interleukin-2, docetaxel, etoposide (VP-16), interferon alfa, paclitaxel, and tretinoin (ATRA); (25) antibiotic natural antineoplastics, such as bleomycin, dactinomycin, daunorubicin, doxorubicin, and mitomycin; (26) vinca alkaloid natural antineoplastics, such as vinblastine and vincristine; (27) autonomic agents, such as nicotine; (28) anticholinergic autonomic agents, such as benztropine and trihexyphenidyl; (29) antimuscarinic anticholinergic autonomic agents, such as atropine and oxybutynin; (30) ergot alkaloid autonomic agents, such as bromocriptine; (31)

cholinergic agonist parasympathomimetics, such as pilocarpine; (32) cholinesterase inhibitor parasympathomimetics, such as pyridostigmine; (33)  $\alpha$ -blocker sympatholytics, such as prazosin; (34)  $\beta$ -blocker sympatholytics, such as atenolol; (35) adrenergic agonist sympathomimetics, such as albuterol and dobutamine; (36) cardiovascular agents, such as aspirin (ASA) (enteric coated ASA); (37)  $\beta$ -blocker antianginals, such as atenolol and propranolol; (38) calcium-channel blocker antianginals, such as nifedipine and verapamil; (39) nitrate antianginals, such as isosorbide dinitrate (ISDN); (40) cardiac glycoside antiarrhythmics, such as digoxin; (41) class I antiarrhythmics, such as lidocaine, mexiletine, phenytoin, procainamide, and quinidine; (42) class II antiarrhythmics, such as atenolol, metoprolol, propranolol, and timolol; (43) class III antiarrhythmics, such as amiodarone; (44) class IV antiarrhythmics, such as diltiazem and verapamil; (45)  $\alpha$ -blocker antihypertensives, such as prazosin; (46) angiotensin-converting enzyme inhibitor (ACE inhibitor) antihypertensives, such as captopril and enalapril; (47)  $\beta$ -blocker antihypertensives, such as atenolol, metoprolol, nadolol, and propranolol; (48) calcium-channel blocker antihypertensive agents, such as diltiazem and nifedipine; (49) central-acting adrenergic antihypertensives, such as clonidine and methyldopa; (50) diuretic antihypertensive agents, such as amiloride, furosemide, hydrochlorothiazide (HCTZ), and spironolactone; (51) peripheral vasodilator antihypertensives, such as hydralazine and minoxidil; (52) antilipemics, such as gemfibrozil and probucol; (53) bile acid sequestrant antilipemics, such as cholestyramine; (54) HMG-CoA reductase inhibitor antilipemics, such as lovastatin and pravastatin; (55) inotropes, such as amrinone, dobutamine, and dopamine; (56) cardiac glycoside inotropes, such as digoxin; (57) thrombolytic agents, such as alteplase (TPA), anistreplase, streptokinase, and urokinase; (58) dermatological agents, such as colchicine, isotretinoin, methotrexate, minoxidil, tretinoin (ATRA); (59)

dermatological corticosteroid anti-inflammatory agents, such as betamethasone and dexamethasone; (60) antifungal topical anti-infectives, such as amphotericin B, clotrimazole, miconazole, and nystatin; (61) antiviral topical anti-infectives, such as acyclovir; (62) topical antineoplastics, such as fluorouracil (5-FU); (63) electrolytic and renal agents, such as lactulose; (64) loop diuretics, such as furosemide; (65) potassium-sparing diuretics, such as triamterene; (66) thiazide diuretics, such as hydrochlorothiazide (HCTZ); (67) uricosuric agents, such as probenecid; (68) enzymes such as RNase and DNase; (69) thrombolytic enzymes, such as alteplase, anistreplase, streptokinase and urokinase; (70) antiemetics, such as prochlorperazine; (71) salicylate gastrointestinal anti-inflammatory agents, such as sulfasalazine; (72) gastric acid-pump inhibitor anti-ulcer agents, such as omeprazole; (73) H<sub>2</sub>-blocker anti-ulcer agents, such as cimetidine, famotidine, nizatidine, and ranitidine; (74) digestants, such as pancrelipase; (75) prokinetic agents, such as erythromycin; (76) opiate agonist intravenous anesthetics such as fentanyl; (77) hematopoietic antianemia agents, such as erythropoietin, filgrastim (G-CSF), and sargramostim (GM-CSF); (78) coagulation agents, such as antihemophilic factors 1-10 (AHF 1-10); (79) anticoagulants, such as warfarin; (80) thrombolytic enzyme coagulation agents, such as alteplase, anistreplase, streptokinase and urokinase; (81) hormones and hormone modifiers, such as bromocriptine; (82) abortifacients, such as methotrexate; (83) antidiabetic agents, such as insulin; (84) oral contraceptives, such as estrogen and progestin; (85) progestin contraceptives, such as levonorgestrel and norgestrel; (86) estrogens such as conjugated estrogens, diethylstilbestrol (DES), estrogen (estradiol, estrone, and estropipate); (87) fertility agents, such as clomiphene, human chorionic gonadatropin (HCG), and menotropins; (88) parathyroid agents such as calcitonin; (89) pituitary hormones, such as desmopressin, goserelin, oxytocin, and vasopressin (ADH); (90) progestins,

such as medroxyprogesterone, norethindrone, and progesterone; (91) thyroid hormones, such as levothyroxine; (92) immunobiologic agents, such as interferon beta-1b and interferon gamma-1b; (93) immunoglobulins, such as immune globulin IM, IMIG, IGIM and immune globulin IV, IVIG, IGIV; (94) amide local anesthetics, such as lidocaine; (95) ester local anesthetics, such as benzocaine and procaine; (96) musculoskeletal corticosteroid anti-inflammatory agents, such as beclomethasone, betamethasone, cortisone, dexamethasone, hydrocortisone, and prednisone; (97) musculoskeletal anti-inflammatory immunosuppressives, such as azathioprine, cyclophosphamide, and methotrexate; (98) musculoskeletal nonsteroidal anti-inflammatory drugs (NSAIDs), such as diclofenac, ibuprofen, ketoprofen, ketorlac, and naproxen; (99) skeletal muscle relaxants, such as baclofen, cyclobenzaprine, and diazepam; (100) reverse neuromuscular blocker skeletal muscle relaxants, such as pyridostigmine; (101) neurological agents, such as nimodipine, riluzole, tacrine and ticlopidine; (102) anticonvulsants, such as carbamazepine, gabapentin, lamotrigine, phenytoin, and valproic acid; (103) barbiturate anticonvulsants, such as phenobarbital and primidone; (104) benzodiazepine anticonvulsants, such as clonazepam, diazepam, and lorazepam; (105) anti-parkinsonian agents, such as bromocriptine, levodopa, carbidopa, and pergolide; (106) anti-vertigo agents, such as meclizine; (107) opiate agonists, such as codeine, fentanyl, hydromorphone, methadone, and morphine; (108) opiate antagonists, such as naloxone; (109)  $\beta$ -blocker anti-glaucoma agents, such as timolol; (110) miotic anti-glaucoma agents, such as pilocarpine; (111) ophthalmic aminoglycoside anti-infectives, such as gentamicin, neomycin, and tobramycin; (112) ophthalmic quinolone anti-infectives, such as ciprofloxacin, norfloxacin, and ofloxacin; (113) ophthalmic corticosteroid anti-inflammatory agents, such as dexamethasone and prednisolone; (114) ophthalmic nonsteroidal anti-inflammatory drugs (NSAIDs), such as diclofenac; (115)

antipsychotics, such as clozapine, haloperidol, and risperidone; (116) benzodiazepine anxiolytics, sedatives and hypnotics, such as clonazepam, diazepam, lorazepam, oxazepam, and prazepam; (117) psychostimulants, such as methylphenidate and pemoline; (118) antitussives, such as codeine; (119) bronchodilators, such as theophylline; (120) adrenergic agonist bronchodilators, such as albuterol; (121) respiratory corticosteroid anti-inflammatory agents, such as dexamethasone; (122) antidotes, such as flumazenil and naloxone; (123) heavy metal antagonists/chelating agents, such as penicillamine; (124) deterrent substance abuse agents, such as disulfiram, naltrexone, and nicotine; (125) withdrawal substance abuse agents, such as bromocriptine; (126) minerals, such as iron, calcium, and magnesium; (127) vitamin B compounds, such as cyanocobalamin (vitamin B<sub>12</sub>) and niacin (vitamin B<sub>3</sub>); (128) vitamin C compounds, such as ascorbic acid; and (129) vitamin D compounds, such as calcitriol.

In addition to the foregoing, the following less common drugs may also be used: chlorhexidine; estradiol cypionate in oil; estradiol valerate in oil; flurbiprofen; flurbiprofen sodium; ivermectin; levodopa; nafarelin; and somatropin.

Further, the following new drugs may also be used: recombinant beta-glucan; bovine immunoglobulin concentrate; bovine superoxide dismutase; the formulation comprising fluorouracil, epinephrine, and bovine collagen; recombinant hirudin (r-Hir), HIV-1 immunogen; human anti-TAC antibody; recombinant human growth hormone (r-hGH); recombinant human hemoglobin (r-Hb); recombinant human mecasermin (r-IGF-1); recombinant interferon beta-1a; lenograstim (G-CSF); olanzapine; recombinant thyroid stimulating hormone (r-TSH); and topotecan.

Further still, the following intravenous products may be used: acyclovir sodium; aldesleukin; atenolol; bleomycin sulfate, human calcitonin; salmon calcitonin; carboplatin; carmustine; dactinomycin, daunorubicin HCl; docetaxel;

doxorubicin HCl; epoetin alfa; etoposide (VP-16);  
fluorouracil (5-FU); ganciclovir sodium; gentamicin sulfate;  
interferon alfa; leuprolide acetate; meperidine HCl;  
methadone HCl; methotrexate sodium; paclitaxel; ranitidine  
5 HCl; vinblastin sulfate; and zidovudine (AZT).

Further specific examples of useful biologically active  
substances from the above categories include: (a) anti-  
neoplastics such as androgen inhibitors, antimetabolites,  
cytotoxic agents, and immunomodulators; (b) anti-tussives  
10 such as dextromethorphan, dextromethorphan hydrobromide,  
noscipine, carbetapentane citrate, and chlorphedianol  
hydrochloride; (c) antihistamines such as chlorpheniramine  
maleate, phenindamine tartrate, pyrilamine maleate,  
doxylamine succinate, and phenyltoloxamine citrate; (d)  
15 decongestants such as phenylephrine hydrochloride,  
phenylpropanolamine hydrochloride, pseudoephedrine  
hydrochloride, and ephedrine; (e) various alkaloids such as  
codeine phosphate, codeine sulfate and morphine; (f) mineral  
supplements such as potassium chloride, zinc chloride,  
20 calcium carbonates, magnesium oxide, and other alkali metal  
and alkaline earth metal salts; (g) ion exchange resins such  
as cholestyramine; (h) anti-arrhythmics such as N-  
acetylprocainamide; (i) antipyretics and analgesics such as  
acetaminophen, aspirin and ibuprofen; (j) appetite  
25 suppressants such as phenyl-propanolamine hydrochloride or  
caffeine; (k) expectorants such as guaifenesin; (l) antacids  
such as aluminum hydroxide and magnesium hydroxide; (m)  
biologicals such as peptides, polypeptides, proteins and  
amino acids, hormones, interferons or cytokines, and other  
30 bioactive peptidic compounds, such as interleukins 1-18  
including mutants and analogues, RNase, DNase, luteinizing  
hormone releasing hormone (LHRH) and analogues, gonadotropin  
releasing hormone (GnRH), transforming growth factor- $\beta$  (TGF-  
 $\beta$ ), fibroblast growth factor (FGF), tumor necrosis factor- $\alpha$   
35 &  $\beta$  (TNF- $\alpha$  &  $\beta$ ), nerve growth factor (NGF), growth hormone  
releasing factor (GHRF), epidermal growth factor (EGF),  
fibroblast growth factor homologous factor (FGFHF),



hepatocyte growth factor (HGF), insulin growth factor (IGF), invasion inhibiting factor-2 (IIF-2), bone morphogenetic proteins 1-7 (BMP 1-7), somatostatin, thymosin- $\alpha$ -1,  $\gamma$ -globulin, superoxide dismutase (SOD), complement factors, hGH, tPA, calcitonin, ANF, EPO and insulin; and (n) anti-infective agents such as antifungals, anti-virals, antiseptics and antibiotics.

Alternatively, the biologically active substance may be a radiosensitizer, such as metoclopramide, sensamide or neusensamide (manufactured by Oxigene); profiromycin (made by Vion); RSR13 (made by Allos); Thymitaq (made by Agouron), etanidazole or lobenguane (manufactured by Nycomed); gadolinium texaphrin (made by Pharmacyclics); BuDR/Broxine (made by NeoPharm); IPdR (made by Sparta); CR2412 (made by Cell Therapeutic); LIX (made by Terrapin); or the like.

Preferably, the biologically active substance is selected from the group consisting of peptides, polypeptides, proteins, amino acids, polysaccharides, growth factors, hormones, anti-angiogenesis factors, interferons or cytokines, and pro-drugs. In a particularly preferred embodiment, the biologically active substance is a therapeutic drug or pro-drug, most preferably a drug selected from the group consisting of chemotherapeutic agents and other anti-neoplastics such as paclitaxel, antibiotics, anti-virals, antifungals, anti-inflammatories, and anticoagulants.

The biologically active substances are used in amounts that are therapeutically effective. While the effective amount of a biologically active substance will depend on the particular material being used, amounts of the biologically active substance from about 1% to about 65% have been easily incorporated into the present delivery systems while achieving controlled release. Lesser amounts may be used to achieve efficacious levels of treatment for certain biologically active substances.

Pharmaceutically acceptable carriers may be prepared from a wide range of materials. Without being limited

thereto, such materials include diluents, binders and adhesives, lubricants, disintegrants, colorants, bulking agents, flavorings, sweeteners and miscellaneous materials such as buffers and adsorbents in order to prepare a particular medicated composition.

#### Implants and Delivery Systems Designed for Injection

In its simplest form, a biodegradable therapeutic agent delivery system consists of a dispersion of the therapeutic agent in a polymer matrix. The therapeutic agent is typically released as the polymeric matrix biodegrades in vivo into soluble products that can be absorbed by and eventually excreted from the body.

In a particularly preferred embodiment, an article is used for implantation, injection, or otherwise placed totally or partially within the body, the article comprising the biodegradable terephthalate polymer composition of the invention. The biologically active substance of the composition and the polymer of the invention may form a homogeneous matrix, or the biologically active substance may be encapsulated in some way within the polymer. For example, the biologically active substance may be first encapsulated in a microsphere and then combined with the polymer in such a way that at least a portion of the microsphere structure is maintained.

Alternatively, the biologically active substance may be sufficiently immiscible in the polymer of the invention that it is dispersed as small droplets, rather than being dissolved, in the polymer. Either form is acceptable, but it is preferred that, regardless of the homogeneity of the composition, the release rate of the biologically active substance in vivo remain controlled, at least partially as a function of hydrolysis of the phosphoester bond of the polymer upon biodegradation.

In a preferred embodiment, the article of the invention is designed for implantation or injection into the body of an animal. It is particularly important that such an

article result in minimal tissue irritation when implanted or injected into vasculated tissue.

As a structural medical device, the polymer compositions of the invention provide a physical form having specific chemical, physical, and mechanical properties sufficient for the application, in addition to being a composition that degrades *in vivo* into non-toxic residues. Typical structural medical articles include such implants as orthopedic fixation devices, ventricular shunts, laminates for degradable fabric, drug-carriers, biosorbable sutures, burn dressings, coatings to be placed on other implant devices, and the like.

In orthopedic articles, the composition of the invention may be useful for repairing bone and connective tissue injuries. For example, a biodegradable porous material can be loaded with bone morphogenetic proteins to form a bone graft useful for even large segmental defects. In vascular graft applications, a biodegradable material in the form of woven fabric can be used to promote tissue ingrowth. The polymer composition of the invention may be used as a temporary barrier for preventing tissue adhesion, e.g., following abdominal surgery.

On the other hand, in nerve regeneration articles, the presence of a biodegradable supporting matrix can be used to facilitate cell adhesion and proliferation. When the polymer composition is fabricated as a tube for nerve generation, for example, the tubular article can also serve as a geometric guide for axonal elongation in the direction of functional recovery.

As a drug delivery device, the polymer compositions of the invention provide a polymeric matrix capable of sequestering a biologically active substance and provide predictable, controlled delivery of the substance. The polymeric matrix then degrades to non-toxic residues.

Biodegradable medical implant devices and drug delivery products can be prepared in several ways. The polymer can be melt processed using conventional extrusion or injection


molding techniques, or these products can be prepared by dissolving in an appropriate solvent, followed by formation of the device, and subsequent removal of the solvent by evaporation or extraction. By these methods, the polymers may be formed into drug delivery systems of almost any size or shape desired, for example, implantable solid discs or wafers or injectable rods, microspheres, or other microparticles.

Once a medical implant article is in place, it should remain in at least partial contact with a biological fluid, such as blood, internal organ secretions, mucous membranes, cerebrospinal fluid and the like.

The following examples are illustrative of preferred embodiments of the invention and are not to be construed as limiting the invention thereto. All polymer molecular weights are average molecular weights. All percentages are based on the percent by weight of the final delivery system or formulation being prepared, unless otherwise indicated, and all totals equal 100% by weight.

#### EXAMPLES

Example 1: Preparation of Monomer Bis(2-hydroxyethyl)terephthalate ("BHET")




25

1.4 moles of dimethyl terephthalate (277 g) and 7.2 moles of ethylene glycol (445 g) were weighed into a one-

liter round-bottomed flask connected to a vacuum line. A catalytic amount of cobalt (II) acetate tetrahydrate (180 mg, 0.5 mole) and calcium acetate hydrate (90 mg, 0.4 mole) were added. The reaction mixture was heated at 160°C in an oil bath under a mild vacuum.


After 18 hours, the reaction was terminated. While still molten, the mixture was poured into cold water. The precipitate formed was collected, dried under vacuum, and redissolved into warm methanol. The sludge (composed largely of oligomers) was filtered off. The filtrate was cooled to -20°C to form a precipitate, which was recrystallized in methanol and ethyl acetate to produce a white powder, the product "BHET".

Alternatively, BHET having excellent purity may be prepared according to the following reaction scheme:



BHET is also commercially available.

Example 2:      Synthesis of Copolymer  
P(BHET-EOP/TC, 80/20)



Under an argon stream, 10 g of 1,4-bis(hydroxyethyl) terephthalate (BHET) prepared as described above in Example 1, 9.61 g of 4-dimethylaminopyridine (DMAP), and 70 mL of methylene chloride were placed in a 250 mL flask equipped with a funnel. The solution in the flask was cooled down to -40°C with stirring, and a solution of 5.13 g of ethyl phosphorodichloridate (EOP) (distilled before use) in 20 mL of methylene chloride was added dropwise through the funnel. After addition was complete, the mixture was stirred at room temperature for four hours to form the homopolymer BHET-EOP.

A solution of 1.60 g of terephthaloyl chloride (TC) (obtained from Aldrich Chemical Company and recrystallized with hexane before use) in 20 mL of methylene chloride was then added drop by drop. The temperature was brought up to about 45-50°C gradually, and the reaction mixture was kept refluxing overnight to complete the copolymerization of the homopolymer P(BHET-EOP) with the additional monomer TC to form the copolymer P(BHET-EOP/TC).

The solvent was then evaporated, and the residue was redissolved in about 100-200 mL of chloroform. The

chloroform solution was washed with a saturated NaCl solution three times, dried over anhydrous Na<sub>2</sub>SO<sub>4</sub>, and quenched into ether. The resulting precipitate was redissolved in chloroform and quenched again into ether. The resulting tough, off-white solid precipitate was filtered off and dried under vacuum. Yield 82%.

The structure of P(BHET-EOP/TC, 80/20) was ascertained by <sup>1</sup>H-NMR, <sup>31</sup>P-NMR and FT-IR spectra, as shown in Figures 2 and 3. The structure was also confirmed by elemental analysis, which correlated closely with theoretical ratios. The results of the elemental analysis are shown in Figure 5.

The molecular weight of P(BHET-EOP/TC, 80/20) was first measured by gel permeation chromatography (GPC) with polystyrene as the calibration standard. The resulting graph established a weight average molecular weight (Mw) of about 6100 and a number average molecular weight (Mn) of about 2200, as shown in Figure 4. Vapor pressure osmometry ("VPO") for this copolymer gave an Mn value of about 7900. The results of these molecular weight studies are also shown in Figure 5.

### Example 3: Feed Ratio Variations of P(BHET-EOP/TC)

A series of other P(BHET-EOP/TC) copolymers of the invention were prepared by following the procedure described above in Example 2 except that the feed ratio of the EOP to TC used during the initial polymerization step and copolymerization step respectively was varied. The results are shown below in Table 1. From the feed ratio of EOP/TC, the value of "x" from the formula shown below can be calculated. For example, in P(BHET-EOP/TC, 80/20) prepared above in Example 2, x is 8.




TABLE 1  
Variation of Feed Ratio of EOP to TC in P(BHET-EOP/TC)

Feed Ratio of EOP/TC*	100/0	95/5	90/10	85/15	80/20	50:50
"x"	-	38	18	11.4	8	2


\*Feed ratio of ethyl phosphorodichloridate to terephthaloyl chloride.

Example 4: Synthesis of Copolymers P(BHET-HOP/TC, 80:20 and 90:10)

The phosphoester copolymers P(BHET-HOP/TC, 80:20) and P(BHET-HOP/TC, 90:10) were prepared by the procedure described above in Example 2, except that hexyl phosphorodichloridate ("HOP") was substituted for the monomer ethyl phosphoro-dichloridate (EOP) during the initial polymerization step, and the feed ratio was varied.

For P(BHET-HOP/TC, 90:10), the elemental analysis, the Mw/Mn value as determined by GPC, and the Mn as determined by VPO, were all ascertained and are shown in Figure 5.


Example 5: Preparation of Monomer Bis(3-hydroxy-2,2'-dimethylpropyl) terephthalate ("BHDPT")




Bis(3-hydroxy-2,2'-dimethylpropyl)terephthalate (BHDPT) was synthesized by reacting terephthaloyl chloride (TC) with an excess of the diol 2,2'-dimethyl-1,3-propanediol in 2-butanone with K<sub>2</sub>CO<sub>3</sub> as the acid acceptor.



Example 6:      Synthesis and Isolation of the Homopolymer  
P(BHDPT-EOP)



5                    The BHDPT monomer prepared in Example 5 above and the  
acid acceptor 4-dimethylaminopyridine (DMAP) were dissolved  
in methylene chloride. The resulting solution was chilled  
to -70°C using a dry ice/acetone bath, and an equal molar  
amount of ethyl phosphorodichloridate (EOP) was slowly  
10                   added. The reaction mixture was then heated and refluxed  
overnight. The salt formed in the polymerization was  
removed by filtration. The remaining polymer solution  
(filtrate) was washed with a saturated NaCl solution three  
times, and the homopolymer was precipitated in diethyl  
15                   ether.

Example 7: Synthesis of Copolymer P(BHDPT-EOP/TC)

Copolymers of P(BHDPT-EOP) with TC were synthesized by  
 the two-step solution copolymerization shown above. After  
 5 the reaction between BHDPT and EOP had proceeded at room  
 temperature for one hour, the reaction flask was cooled in a  
 dry ice/acetone bath. An appropriate amount of TC (the  
 number of moles of TC and EOP combined equaled the number of  
 moles of BHDPT) was slowly added to the flask. The reaction  
 10 mixture was then heated and refluxed overnight. The salt  
 formed in the polymerization was removed by filtration. The  
 remaining copolymer solution (filtrate) was washed with a  
 saturated NaCl solution three times, and the copolymer was  
 precipitated out in diethyl ether.

Example 8: Feed Ratio Variations for P(BHDPT-EOP/TC)

A series of other P(BHDPT-EOP/TC) copolymers of the invention were prepared by following the procedure described above in Example 7, except that the feed ratio of EOP to TC, which were used during the initial polymerization step and the copolymerization step respectively, were varied. The results are shown below in Table 2. From the feed ratio of EOP/TC, the value of x from the formula shown below can be calculated. For example, in P(BHDPT-EOP/TC, 80/20), the value of x is 8.





TABLE 2  
Variation of Feed Ratio of EOP to TC in P(BHDPT-EOP/TC)

Feed Ratio of EOP/TC*	100/0	90/10	85/15	80/20	75/25	50:50
"x"	-	18	11.4	8	6	2


\*Feed ratio of ethyl phosphorodichloridate to terephthaloyl chloride.

Example 9: Synthesis and Isolation of the Homopolymer P(BHDPT-HOP)

The BHDPT monomer prepared in Example 5 above and the acid acceptor 4-dimethylaminopyridine (DMAP) were dissolved

in methylene chloride. The resulting solution was chilled to  $-70^{\circ}\text{C}$  using a dry ice/acetone bath, and an equal molar amount of hexyl phosphorodichloridate (HOP) was slowly added. The reaction mixture was then heated and refluxed overnight. The salt formed in the polymerization was removed by filtration. The remaining polymer solution (filtrate) was washed with a saturated NaCl solution three times, and the homopolymer was precipitated in diethyl ether.

Example 10:      Synthesis of Poly(phosphoester) P(BHDPT-HOP/TC)




Copolymers of P(BHDPT-HOP) with TC were synthesized by a two-step solution polymerization. After the reaction between BHDPT and HOP had proceeded at room temperature for one hour, the reaction flask was cooled in a dry ice/acetone bath. An appropriate amount of TC (the number of moles of

TC and HOP combined equaled the number of moles of BHDPT) was slowly added to the flask. The reaction mixture was then heated and refluxed overnight. The salt formed during the copolymerization was removed by filtration. The remaining copolymer solution (filtrate) was washed with a saturated NaCl solution three times, and the copolymer was precipitated out in diethyl ether.

Example 11: Other Diol Variations

Diol terephthalates that are structurally related to that of BHET and BHDPT were synthesized similarly to that in Example 5 by reacting TC with either n-propylenediol or 2-methylpropylenediol, the structures of which are shown below, to form the corresponding diol terephthalate.



These diol terephthalates were then reacted with EOP to form the corresponding homopolymers. The homopolymers so formed were then used to produce the copolymers of the invention in a second reaction with TC, as described above in Example 7.

Example 12: Glass Transition Temperatures for P(BHET-EOP/TC) Copolymers

By differential scanning calorimetry (DSC), the glass transition temperatures (Tg's) of P(BHET-EOP/TC, 80/20) and P(BHET-EOP/TC, 50/50) were determined to be 24.5°C and 62.2°C respectively. Figure 1 shows the DSC curves for these two polymers. The Tg's of four additional P(BHET-EOP/TC) copolymers of differing EOP/TC feed ratios were determined, and the results were tabulated, as shown below in Table 3:

TABLE 3  
Glass Transition Temperatures (Tg's)  
of (BHET-EOP/TC) Polymers

Ratio of EOP/TC*	100/0	95/5	90/10	85/15	80/20	50:50
Tg (°C)	19.1	20.7	21.2	29.8	24.5	62.2

\*Feed ratio of ethyl phosphorodichloridate to terephthaloyl chloride

The Tg increased as the proportion of EOP decreased and the proportion of TC increased.

Example 14:      Glass Transition Temperatures  
                         for P(BHDPT-EOP/TC) Copolymers

A study of the influence of an increasing proportion of terephthaloyl chloride (TC) on the Tg's of P(BHDPT-EOP/TC) polymers was also conducted. The results are shown below in Table 4.


TABLE 4  
Influence of EOP/TC Ratio on the Tg of P(BHDPT-EOP/TC)

Molar ratio (BHDPT/EOP/TC) *	Tg (°C)
100:100:0	14
100:100:0	19
100:90:10	16
100:85:15	23
100:80:20	23
100:75:25	33
100:75:25	49
100:50:50	43

\*The total molar amount of TC and EOP equaled the molar amount of BHDPT.

Example 15:      Glass Transition Temperatures for Various R  
                         Groups

A study was also conducted showing the effect on glass transition temperature (Tg) for copolymers made from the following series of diols having varying R groups:



where R is  $-\text{CH}_2\text{CH}_2-$ ;  $-\text{CH}_2\text{CH}_2\text{CH}_2-$ ;  $-\text{CH}_2\text{CH}(\text{CH}_3)\text{CH}_2-$ ; and  $-\text{CH}_2\text{CH}(\text{CH}_3)_2\text{CH}_2-$ . The results are shown below in Table 5:

TABLE 5  
Influence of the Changing "R" Group on Tg of Polymer

"R" Group	Structure	Tg (°C)
ethylene	$-\text{CH}_2\text{CH}_2-$	14-19
n-propylene	$-\text{CH}_2\text{CH}_2\text{CH}_2-$	-15
2-methylpropylene	$\begin{array}{c} -\text{CH}_2\text{CHCH}_2- \\   \\ \text{CH}_3 \end{array}$	11
2,2'-dimethylpropylene	$\begin{array}{c} \text{CH}_3 \\   \\ -\text{CH}_2\text{CCH}_2- \\   \\ \text{CH}_3 \end{array}$	19

As shown in Table 5, the Tg increased as the size and the degree of branching of the R group increased. In addition, the polymers changed in physical state as the Tg changed. Specifically, as Tg increased, the polymers changed from rubbery to fine powders.

Example 16: Solubilities of the Polymers of the Invention

The solubility in organic solvents was determined for the homopolymer P(BHET-EOP, 100/0) and for the following block copolymers: P(BHET-EOP/TC, 95/5),

5 P(BHET-EOP/TC, 90/10),  
P(BHET-EOP/TC, 85/15),  
P(BHET-EOP/TC, 80/20), and  
P(BHET-EOP/TC, 50/50).

10 The organic solvents used for the test were chloroform, methylene chloride, N-methylpyrrolidone (NMP), dimethylformamide (DMF) and dimethylsulfoxide (DMSO). The results of these solubility tests are summarized below in Table 6.

TABLE 6

15	Polymer	CHCl <sub>3</sub>	CH <sub>2</sub> Cl <sub>2</sub>	NMP	DMF	DMSO
	P(BHET-EOP, 100/0)	Easily soluble	Easily soluble	Good solubility	Good solubility	Good solubility
20	P(BHET-EOP/TC, 95/5)	Easily soluble	Easily soluble	Good solubility	Good solubility	Good solubility
	P(BHET-EOP/TC, 90/10)	Easily soluble	Easily soluble	Good solubility	Good solubility	Good solubility
25	P(BHET-EOP/TC, 85/15)	Relatively soluble	Relatively soluble	Good solubility	Good solubility	Good solubility
30	P(BHET-EOP/TC, 80/20)	Relatively soluble	Relatively soluble	Good solubility	Good solubility	Good solubility
	P(BHET-EOP/TC, 50/50)	Not soluble	Not soluble	Soluble with heating	Soluble with heating	Soluble with heating

35 The results showed that the solubility of these polymers in organic solvents increased as the EOP/TC ratio increased.



Example 16: Viscosities of the Polymers

The intrinsic viscosities of a series of P(BHET-EOP/TC) polymers of varying feed ratios were measured in chloroform (CH<sub>2</sub>Cl) at 40°C in a Ubbelohde viscometer. The results are shown below in Table 7.

TABLE 7  
Intrinsic Viscosities of P(BHET-EOP/TC) Polymers

Ratio of EOP/TC*	100/0	95/5	90/10	85/15	80/20	50:50
[ $\eta$ ] (dL/g)	0.081	0.089	0.148	0.146	0.180	N.D.†

\*Feed ratio of ethyl phosphorodichloridate to terephthaloyl chloride.

†The intrinsic viscosity of P(BHET-EOP/TC, 50/50) was not determined because it was not soluble in chloroform.

Example 17: Physical Properties

Film sheets were prepared by solvent casting a series of P(BHET-EOP/TC) copolymers having various feed ratios. Both P(BHET-EOP/TC, 80/20) and P(BHET-EOP/TC, 85/15) copolymers exhibited good film forming properties. For these two copolymers, also, polymer fibers were successfully drawn from the copolymer melt at 160°C.

Example 18: Stability Testing

(BHET-EOP/TC) copolymers of the invention were placed in a desiccator at room temperature, and their stability was monitored by intrinsic viscosity and GPC. The copolymers were stable under these conditions without the need for storage under inert gas.

Samples of P(BHET-EOP/TC 80/20) and P(BHET-EOP/TC 85/15) were also stored for one month in room air at room temperature. The stability was tested by intrinsic viscosity at the end of the one-month period, and the results are graphically represented in Figure 6.

Example 19: In vitro Degradation

Films of P(BHET-EOP/TC, 80/20) and P(BHET-EOP/TC, 85/15) were made by solution casting methods, as prepared in Example 18, and were dried under vacuum for 2 days. Discs 1 mm in thickness and 6 mm in diameter were cut from these film sheets. Three discs of each copolymer were placed in 4 mL of phosphate buffer saline (PBS) (0.1M, pH 7.4) at 37°C. The discs were taken out of the PBS at different points in time, washed with distilled water, and dried overnight.

The samples were analyzed for change in molecular weight and weight loss over time, as shown in Figures 7A and 7B. The weight average molecular weight of P(BHET-EOP/TC, 80/20) decreased about 20% in three days. After 18 days, the P(BHET-EOP/TC, 85/15) and P(BHET-EOP/TC, 80/20) discs had lost about 40% and 20% in mass respectively.

This data demonstrated the feasibility of fine-tuning the degradation rate of the copolymers and confirmed that the copolymers became more hydrolytically labile as the phosphate component (EOP) was increased.

The same process was repeated for the P(BHDPT-EOP) polymers synthesized in Examples 6-8 above, including copolymers having different feed ratios of EOP to TC. Figure 8 is a graphic representation of the degree of degradation, as measured by change in molecular weight, over time for the homopolymer P(BHDPT-EOP) and the following block copolymers:

P(BHDPT-EOP/TC, 85/15),  
P(BHDPT-EOP/TC, 75/25), and  
P(BHDPT-EOP/TC, 50/50).

Example 20: In vivo Degradation of P(BHET-EOP/TC) Copolymer

Figure 9 shows the *in vivo* degradation of P(BHET-EOP/TC, 80/20), as measured by weight loss.

Example 21:     In vitro Biocompatibility/  
Cytotoxicity of P(BHET-EOP/TC, 80/20)

The cytotoxicity of P(BHET-EOP/TC, 80/20) copolymer was assessed by culturing human embryonic kidney (HEK) cells on a cover slip that had been coated with the copolymer P(BHET-EOP/TC, 80/20). As a control, HEK cells were also cultured on a coverslip coated with TCPS. The cells cultured on the copolymer-coated cover slip exhibited normal morphology at all times and proliferated significantly in 72 days, as compared to a considerably lower amount when identical HEK cells were cultured on TCPS.

Example 22:     In vivo Biocompatibility of P(BHET-EOP/TC,  
80/20)

A 100 mg polymer wafer was formed from P(BHET-EOP/TC, 80/20) and, as a reference, a copolymer of lactic and glycolic acid (75/25, "PLGA") known to be biocompatible. These wafers were inserted between muscle layers of the right limb of adult SPF Sprague-Dawley rats under anesthesia. The wafers were retrieved at specific times, and the surrounding tissues were prepared for histopathological analysis by a certified pathologist using the following scoring:

<u>Score</u>	<u>Level of Irritation</u>
0	No Irritation
0 - 200	Slight Irritation
200 - 400	Mild Irritation
400 - 600	Moderate Irritation
More than 600	Severe Irritation

The results of the histopathological analysis are shown below in Table 8.

TABLE 8  
Inflammatory Response at Site of Implantation (i.m.)

Polymer	3 Days	7 Days	14 Days	1 Month	2 Mos.	3 Mos.
P(BHET- EOP/TC, 80/20)	151	116	163	98	60	35
PLGA (75/25)	148	98	137	105	94	43

The phosphoester copolymer P(BHET-EOP/TC, 80/20) was shown to have an acceptable biocompatibility similar to that exhibited by the PLGA reference wafer.

Example 23: Preparation of P(BHET-EOP/TC, 80/20)  
Microspheres Encapsulating FITC-BSA

Microspheres were prepared via a double-emulsion/solvent-extraction method using FITC-labeled bovine serum albumin (FITC-BSA) as a model protein drug. One hundred  $\mu$ L of an FITC-BSA solution (10 mg/mL) were added to a solution of 100 mg of P(BHET-EOP/TC, 80/20) in 1 mL of methylene chloride, and emulsified via sonication for 15 seconds on ice. The resulting emulsion was immediately poured into 5 mL of a vortexing aqueous solution of 1% polyvinyl alcohol (PVA) and 5% NaCl. The vortexing was maintained for one minute. The resulting emulsion was poured into 20 mL of an aqueous solution of 0.3% PVA and 5% NaCl, which was being stirred vigorously. Twenty-five mL of a 2% isopropanol solution was added, and the mixture was kept stirring for one hour to ensure complete extraction. The resulting microspheres were collected via centrifugation at 3000 X g, washed three times with water, and lyophilized. Empty microspheres were prepared in the same way except that water was used as the inner aqueous phase.

These preparation conditions had been optimized for increased encapsulation efficiency, improved microsphere morphology, and minimal burst release. The resulting microspheres were mostly between 5 and 20  $\mu$ m in diameter and

exhibited a smooth surface morphology. Figure 10 shows the size and smoothness of the microspheres, as demonstrated by electron microscopy.

The loading level of FITC-BSA was determined by assaying for FITC after hydrolyzing the microspheres in a 0.5 N NaOH solution overnight. Loading levels were determined by comparison with a standard curve, which had been generated by making a series of FITC-BSA solutions in 0.5 N NaOH. Protein loading levels of 1.5, 14.1 and 22.8 wt.% were readily obtained.

The encapsulation efficiency of FITC-BSA by the microspheres was determined at different loading levels by comparing the quantity of FITC-BSA entrapped with the initial amount in solution via fluorometry. As shown below in Table 9, encapsulation efficiencies of 84.6 and 99.6% were obtained. These results showed that encapsulation efficiencies of 70-90% would be readily obtainable.

TABLE 9  
Encapsulation Efficiency and Loading  
Level of FITC-BSA in P(BHET-EOP/TC,  
80/20)

Loading (%)	High Loading (22.8%)	Low Loading (1.5%)
Encapsulation Efficiency (%)	99.6	84.6

In addition, it was determined by observation with confocal fluorescence microscopy that the encapsulated FITC-BSA was distributed uniformly within the microspheres.

Example 24:      Preparation of P(BHDPT-EOP/TC, 50/50)  
                         Microspheres Containing Lidocaine

An aqueous solution of 0.5% w/v polyvinyl alcohol (PVA) was prepared in a 600 mL beaker by combining 1.35 g of PVA with 270 mL of deionized water. The solution was stirred for one hour and filtered. A copolymer/drug solution was prepared by combining 900 mg of P(BHDPT-EOP/TC, 50/50)

copolymer and 100 mg of lidocaine in 9 mL of methylene chloride and vortex-mixing.

While the PVA solution was being stirred at 800 rpm with an overhead mixer, the polymer/drug mixture was added dropwise. The combination was stirred for one and a half hours. The microspheres thus formed were then filtered, washed with deionized water, and lyophilized overnight. The experiment yielded 625 mg of microspheres loaded with 3.7% w/w lidocaine.

Lidocaine-containing microspheres were also prepared from P(BHDPT-HOP/TC, 50/50) by the same process. This experiment yielded 676 mg of microspheres loaded with 5.3% w/w lidocaine.

Example 25: In vitro Release Kinetics of Microspheres Prepared from P(BHET-EOP/TC, 80/20) Copolymers

Five mg of P(BHET-EOP/TC, 80/20) microspheres containing FITC-BSA were suspended in one mL of phosphate buffer saline (PBS) at pH 7.4 and placed into a shaker heated to a temperature of 37°C. At various points in time, the suspension was spun at 3000 X g for 10 minutes, and 500 µl samples of the supernatant fluid were withdrawn and replaced with fresh PBS. The release of FITC-BSA from the microspheres was followed by measuring the fluorescence intensity of the withdrawn samples at 519 nm.

Scaling up, 50 mg of P(BHET-EOP/TC, 80/20) microspheres were suspended in vials containing 10 mL of phosphate buffer saline (PBS). The vials were heated in an incubator to a temperature of 37°C and shaken at 220 rpm. Samples of the supernatant were withdrawn and replaced at various points in time, and the amount of FITC-BSA released into the samples was analyzed by spectrophotometry at 492 nm.

The results indicated that over 80% of the encapsulated FITC-BSA was released within the first two days, with an additional amount of about 5% being released after 10 days in PBS at 37°C. The release kinetics of FITC-BSA from

P(BHET-EOP/TC, 80/20) microspheres at different loading levels are shown in Figure 11.

5     Example 26:     In vitro Release Kinetics of Microspheres  
                            Prepared from P(BHDPT-EOP/TC, 50/50)  
                            Copolymers

10             Approximately 10 mg of P(BHDPT-EOP/TC, 50/50)  
                    microspheres loaded with lidocaine were placed in PBS (0.1  
                    M, pH 7.4) at 37°C on a shaker. Samples of the incubation  
                    solution were withdrawn periodically, and the amount of  
                    lidocaine released into the samples was assayed by HPLC.  
                    Figures 12 and 13 show the resulting release kinetics.

15             The same process was followed for microspheres prepared  
                    from P(BHDPT-HOP/TC, 50/50). Figures 12 and 13 also show  
                    the release kinetics of lidocaine from these microspheres.

20     Example 28:     In vitro Cytotoxicity Assay of Copolymer on  
                            Cells

25             P(BHET-EOP/TC, 80/20) microspheres were added to 96-  
                    well tissue culture plates at different concentrations. The  
                    wells were then seeded with human gastric carcinoma cells  
                    (GT3TKB) at a density of  $10^4$  cells/well. The cells were  
                    incubated with the microspheres for 48 hours at 37°C. The  
                    resulting cell proliferation rate was analyzed by MTT assay  
                    and plotted as % relative growth vs. concentration of  
                    copolymer microspheres in the tissue culture well. The  
                    results are shown in Figure 14.

30     Example 28:     Toxicity Assay of Polymer-Degradation  
                            Products on GT3TKB Tumor Cells

35             About 100-150 mg of each of the following polymers were  
                    degraded separately in 20 mL of 1M NaOH at 37°C for 1-2  
                    days:

                            PLLA (Mw = 14,000)

                            P(BHET-EOP)

                            PCPP:SA (20:80)

40                             Poly(L-lysine) (Mw = 88,000)

Complete degradation was observed for all of the polymers. The solution was then neutralized with 20 mL of 1M HCl.

5 About 200  $\mu$ L of various concentrations of the degraded polymer products were placed in 96-well tissue culture plates and seeded with human gastric carcinoma cells (GT3TKB) at a density of  $10^4$ /well. The degraded polymer products were incubated with the GT3TKB cells for 48 hours. The results of the assay were plotted as % relative growth vs. concentration of degraded polymer in the tissue-culture well and are shown in Figure 15.


10 An additional toxicity assay was conducted with microspheres prepared from the monomer BHET and from the homopolymer BHET-EOP, and compared with microspheres prepared from LA and PLLA. The results of the assay were plotted as % relative growth vs. concentration of the polymers or microspheres in a tissue-culture cell and are shown in Figure 16.

15 The invention being thus described, it will be obvious that the same may be varied in many ways. Such variations are not to be regarded as a departure from the spirit and scope of the invention, and all such modifications are intended to be included within the scope of the following claims.



We claim:

1. A biodegradable terephthalate polymer comprising the recurring monomeric units shown in formula I:



wherein R is a divalent organic moiety;


R' is an aliphatic, aromatic or heterocyclic residue;

x is  $\geq 1$ ; and

n is 0-5,000,

wherein said biodegradable polymer is biocompatible before and upon biodegradation.

2. The polymer of claim 1 wherein R is an alkylene group, a cycloaliphatic group, a phenylene group, or a divalent group having the formula:



wherein X is oxygen, nitrogen, or sulfur, and

n is 1 to 3.

3. The polymer of claim 1 wherein R is an alkylene group having from 1 to 7 carbons atoms.

4. The polymer of claim 1 wherein R is an ethylene group.

5. The polymer of claim 1 wherein R is an n-propylene group.

6. The polymer of claim 1 wherein R is 2-methylpropylene.

7. The polymer of claim 1 wherein R is 2,2'-dimethyl-propylene.

5 8. The polymer of claim 1 wherein R' is an alkyl group or a phenyl group.

9. The polymer of claim 1 wherein R' is an alkyl group having from 1 to 7 carbon atoms.

10 10. The polymer of claim 1 wherein R' is an ethyl group.

11. The polymer of claim 1 wherein x is from about 1 to about 30.

15 12. The polymer of claim 1 wherein x is from about 1 to about 20.


20 13. The polymer of claim 1 wherein x is from about 2 to about 20.

14. The polymer of claim 1 wherein said polymer is prepared by solution polymerization.

25 15. The polymer of claim 1 wherein said polymer comprises additional biocompatible monomeric units.

30 16. The polymer of claim 1 wherein said polymer is soluble in at least one of the solvents selected from the group consisting of acetone, dimethylene chloride, chloroform, ethyl acetate, DMAC, N-methyl pyrrolidone, dimethylformamide and dimethylsulfoxide.

35 17. A process for preparing a biodegradable terephthalate homopolymer comprising the recurring monomeric units of formula I:




wherein R is a divalent organic moiety;

R' is an aliphatic, aromatic or heterocyclic residue;


x is  $\geq 1$ ; and

5 n is 0-5,000,


wherein said biodegradable polymer is biocompatible before and upon biodegradation, said process comprising the step of polymerizing p moles of a diol compound having formula II:



10 wherein R is as defined above, with q moles of a phosphorodichloridate of formula III:



wherein R' is defined as above, and  $p > q$ , to form q moles of a homopolymer of formula IV, shown below:



15 wherein R, R' and x are as defined above.

18. The process of claim 17 wherein R is an alkylene group having from 1 to 7 carbon atoms.

20

19. The process of claim 17 wherein R is an ethylene group.

20. The process of claim 17 wherein R is an n-propylene group.

5 21. The process of claim 17 wherein R is 2-methylpropylene.

22. The process of claim 17 wherein R is 2,2'-dimethylpropylene.

10 23. The process of claim 17 wherein R' is an alkyl group having from 1 to 7 carbon atoms.

15 24. The process of claim 17 wherein R' is an ethyl group.

25. The process of claim 17 wherein x is from about 1 to about 40.

20 26. The process of claim 17 wherein said polymerization reaction takes place at a temperature about -40 to about +160°C.

25 27. The process of claim 17 wherein the temperature of the polymerization varies from about 0 to 65°C.


28. The process of claim 17 wherein said polymerization takes place during a time between about 30 minutes and 24 hours.

30 29. The process of claim 17 wherein said polymerization is a solution polymerization reaction.

35 30. The process of claim 17 wherein an acid acceptor is present.

31. The process of claim 17 wherein the acid acceptor is a tertiary amine.


32. A process for preparing a biodegradable terephthalate polymer comprising the recurring monomeric units of formula I:




5        wherein R is a divalent organic moiety;  
              R' is an aliphatic, aromatic or heterocyclic residue;  
              x is  $\geq 1$ ; and  
              n is 0-5,000.

wherein said biodegradable polymer is biocompatible before  
10 and upon biodegradation, said process comprising the steps  
of:


(a) polymerizing p moles of a diol compound having formula II:



15            wherein R is as defined above, with q moles of a  
phosphorodichloridate of formula III:




wherein R' is defined as above, and  $p > q$ , to form q moles of a polymer of formula IV, shown below:



wherein R, R' and x are as defined above; and

- (b) further reacting said polymer of formula IV and excess diol of formula II with (p - q) moles of terephthaloyl chloride having the formula V:



5 to form said polymer of formula I.

33. The process of claim 32 wherein R is an alkylene group having from 1 to 7 carbon atoms.

10 34. The process of claim 32 wherein R is an ethylene group.

35. The process of claim 32 wherein R is an n-propylene group.

15 36. The process of claim 32 wherein R is 2-methylpropylene.

20 37. The process of claim 32 wherein R is 2,2'-dimethylpropylene.

38. The process of claim 32 wherein R' is an alkyl group having from 1 to 7 carbon atoms.

25 39. The process of claim 32 wherein R' is an ethyl group.

40. The process of claim 32 wherein x is from about 1 to 30.

30 41. The process of claim 32 wherein x is from about 2 to about 20.

42. The process of claim 32 wherein said polymerization reaction of step (a) takes place at a temperature about -40 to about +160°C.

5           43. The process of claim 32 wherein the temperature of the polymerization step (a) varies from about 0 to 65°C.

10           44. The process of claim 32 wherein said polymerization step (a) takes place during a time between about 30 minutes and 24 hours.

          45. The process of claim 32 wherein said polymerization step (a) is a solution polymerization reaction.

15           46. The process of claim 32 wherein an acid acceptor is present during said polymerization step (a).

20           47. The process of claim 32 wherein the acid acceptor is a tertiary amine.

          48. The process of claim 32 wherein said copolymerization of step (b) takes place at a temperature between about -40 and 100°C.

25           49. The process of claim 32 wherein said copolymerization of step (b) takes place during a time of about 30 minutes to 24 hours.

30           50. The process of claim 32 wherein said polymer of formula I is purified by quenching a solution of said polymer with a non-solvent or a partial solvent.

35           51. A biosorbable suture comprising the polymer of claim 1.


52. An orthopedic appliance, bone cement or bone wax for repairing injuries to bone and connective tissue comprising the polymer of claim 1.

53. A laminate for degradable or non-degradable fabrics comprising the polymer of claim 1.

54. A coating for an implantable device comprising the polymer of claim 1.

55. A biodegradable terephthalate polymer composition comprising:

- (a) at least one biologically active substance and
- (b) a polymer having the recurring monomeric units shown in formula I:



wherein R is a divalent organic moiety;


R' is an aliphatic, aromatic or heterocyclic residue;

x is  $\geq 1$ ;

n is 0-5,000; and

said polymer is biocompatible before and upon biodegradation.

56. The polymer composition of claim 55 wherein R is an alkylene group, a cycloaliphatic group, a phenylene group, or a divalent group having the formula:



wherein X is oxygen, nitrogen, or sulfur,

and n is 1 to 3.



57. The polymer composition of claim 55 wherein R is an ethylene group.

5 58. The polymer composition of claim 55 wherein R is an n-propylene group.

59. The polymer composition of claim 55 wherein R is 2-methylpropylene.

10 60. The polymer composition of claim 55 wherein R is 2,2'-dimethylpropylene.

15 61. The polymer composition of claim 55 wherein R' is an alkyl group or a phenyl group.

62. The polymer composition of claim 55 wherein R' is an ethyl group.

20 63. The polymer composition of claim 55 wherein x is from about 1 to about 30.

64. The polymer composition of claim 55 wherein said copolymer is prepared by solution polymerization.

25 65. The polymer composition of claim 55 wherein said polymer comprises additional biocompatible monomeric units.

30 66. The polymer composition of claim 55 wherein said polymer is soluble in at least one of the solvents selected from the group consisting of acetone, dimethylene chloride, chloroform, ethyl acetate, DMAC, N-methyl pyrrolidone, dimethylformamide and dimethylsulfoxide.

35 67. The polymer composition of claim 55 wherein said biologically active substance is selected from the group consisting of peptides, polypeptides, proteins, amino acids, polysaccharides, growth factors, hormones, anti-angiogenesis

factors, interferons or cytokines, and pro-drugs of these substances.

5 68. The polymer composition of claim 55 wherein said biologically active substance is a therapeutic drug or pro-drug.


10 69. The polymer composition of claim 68 wherein said drug is selected from the group consisting of anti-neoplastic agents, antibiotics, anti-virals, antifungals, anti-inflammatories, and anticoagulants.

15 70. The polymer composition of claim 55 wherein said biologically active substance and said polymer form a homogeneous matrix.

20 71. The polymer composition of claim 55 wherein said polymer is characterized by a release rate of the biologically active substance *in vivo* controlled at least partially as a function of hydrolysis of the phosphoester bond of the polymer during biodegradation.

25 72. An article useful for implantation, injection, or otherwise placed totally or partially within the body, said article comprising a biodegradable terephthalate polymer composition comprising:

- (a) at least one biologically active substance and
- (b) a polymer having the recurring monomeric units shown in formula I:



30

wherein R is a divalent organic moiety;


R' is an aliphatic, aromatic or heterocyclic residue;

x is  $\geq 1$ ; and

n is 0-5,000,

wherein said polymer is sufficiently pure to make the biodegradable composition biocompatible upon biodegradation.

- 5           73. The article of claim 72 wherein R is an alkylene group, a cycloalkylene group, a phenylene group, or a divalent group having the formula:



- 10           wherein X is oxygen, nitrogen, or sulfur, and  
              n is 1 to 3.

74. The article of claim 72 wherein R is an ethylene group.

- 15           75. The article of claim 72 wherein R is an n-propylene group.

76. The article of claim 72 wherein R is 2-methylpropylene.

- 20           77. The article of claim 72 wherein R is 2,2'-dimethylpropylene.

- 25           78. The article of claim 72 wherein R' is an alkyl group or a phenyl group.

79. The article of claim 72 wherein R' is an ethyl group.

- 30           80. The article of claim 72 wherein x is from about 1 to about 30.

81. The article of claim 72 wherein x is from about 2 to 20.

5 82. The article of claim 72 wherein said polymer is prepared by solution polymerization.

83. The article of claim 72 wherein said polymer comprises additional biocompatible monomeric units.

10 84. The article of claim 72 wherein said polymer is soluble in at least one of the solvents selected from the group consisting of acetone, dimethylene chloride, chloroform, ethyl acetate, DMAC, N-methyl pyrrolidone, dimethylformamide and dimethylsulfoxide.

15 85. The article of claim 72 wherein said biologically active substance is selected from the group consisting of peptides, polypeptides, proteins, amino acids, poly-saccharides, growth factors, hormones, anti-angiogenesis factors, interferons or cytokines, and pro-drugs of these substances.

20 86. The article of claim 72 wherein said biologically active substance is a therapeutic drug or pro-drug.

25 87. The article of claim 86 wherein said biologically active substance is selected from the group consisting of anti-neoplastic agents, antibiotics, anti-virals, antifungals, anti-inflammatories, anticoagulants, and pro-drugs of these substances.

30 88. The article of claim 72 wherein said biologically active substance and said polymer form a homogeneous matrix.

35 89. The article of claim 72 wherein said biologically active substance is encapsulated within said polymer.

90. The article of claim 72 wherein said polymer is characterized by a release rate of the biologically active substance *in vivo* controlled at least partially as a function of hydrolysis of the phosphoester bond of the polymer upon biodegradation.

91. The article of claim 72 wherein said article is adapted for implantation or injection into the body of an animal.


92. The article of claim 72 wherein said article results in minimal tissue irritation when implanted or injected into vasculated tissue.

93. The article of claim 72 wherein said article is in the form of a laminate for degradable fabric.

94. The article of claim 72 wherein said article is in the form of a biosorbable suture, a material for repairing bone injuries, or a coating on an implant device.

95. A method for the controlled release of a biologically active substance comprising the steps of:

- (a) combining the biologically active substance with a biodegradable terephthalate polymer having the recurring monomeric units shown in formula I:



wherein R is a divalent organic moiety;

R' is an aliphatic, aromatic or heterocyclic residue;

x is  $\geq 1$ ; and

n is 0-5,000,

wherein said polymer is biocompatible before and upon biodegradation, to form an admixture;

- (b) forming said admixture into a shaped, solid article; and
- (c) implanting or injecting said solid article *in vivo* at a preselected site, such that the solid implanted or injected matrix is in at least partial contact with a biological fluid.

96. The method of claim 95 wherein R is an ethylene group.

97. The method of claim 96 wherein R is an n-propylene group.

98. The method of claim 96 wherein R is 2-methylpropylene.

99. The method of claim 96 wherein R is 2,2'-dimethylpropylene.

100. The method of claim 96 wherein R' is an ethyl group.

101. The method of claim 96 wherein x is from about 1 to about 30.

102. The method of claim 96 wherein the ratio is from about 10:1 to about 1:1.

103. The method of claim 96 wherein said polymer comprises additional biocompatible monomeric units.

104. The method of claim 96 wherein said biologically active substance is selected from the group consisting of peptides, polypeptides, proteins, amino acids, polysaccharides, growth factors, hormones, anti-angiogenesis factors and other anti-neoplastic agents, interferons or cytokines, and pro-drugs of these substances.

105. The method of claim 96 wherein said biologically active substance is a therapeutic drug or pro-drug.

5 106. The method of claim 96 wherein said drug is selected from the group consisting of chemotherapeutic agents, antibiotics, anti-virals, antifungals, anti-inflammatory, and anticoagulants.

10 107. The method of claim 96 wherein said biologically active substance and said polymer form a homogeneous matrix.

15 108. The method of claim 96 further comprising encapsulating said biologically active substance within said polymer.

20 109. The method of claim 96 wherein said polymer is characterized by a release rate of the biologically active substance in vivo controlled at least partly as a function of hydrolysis of the phosphoester bond of the polymer upon degradation.

25 110. The method of claim 96 wherein said article is non-toxic and results in minimal tissue irritation when implanted or injected into vasculated tissue.

111. The method of claim 96 wherein said article is in the form of a laminate for degradable fabric.

30 112. The method of claim 96 wherein said polymer composition is used as a coating for an implant.

113. The method of claim 96 wherein the polymer composition is used as a barrier for adhesion prevention.

35 114. The method of claim 96 wherein said polymer composition is fabricated as a tube for nerve generation.

1 / 15

FIG. 1A





FIG. 1B





2 / 15

## FIG. 2A

80/20-B, DMSO

OBSERVE H1

FREQUENCY 399.952 MHz

SPECTRAL WIDTH 5000.0 Hz

ACQUISITION TIME 3.744 sec

RELAXATION DELAY 0.000 sec

PULSE WIDTH 7.0  $\mu$ sec

AMBIENT TEMPERATURE


NO. REPETITIONS 12

DOUBLE PRECISION ACQUISITION

DATA PROCESSING

FT SIZE 65536

TOTAL ACQUISITION TIME 1 minute



## FIG. 2B

80/20-B,BB, DMSO

OBSERVE P31

FREQUENCY 161.903 MHz

SPECTRAL WIDTH 16000.0 Hz

ACQUISITION TIME 0.800 sec

RELAXATION DELAY 0.000 sec

PULSE WIDTH 10.0  $\mu$ sec

TEMPERATURE 37.0°C

NO. REPETITIONS 77

DECOUPLE H1

HIGH POWER 33

DECOUPLER CONTINUOUSLY ON

WALTZ16 MODULATED


DOUBLE PRECISION ACQUISITION

DATA PROCESSING

LINE BROADENING 15.0Hz


FT SIZE 32768

TOTAL ACQUISITION TIME 1 minute



3 / 15

FIG. 3



4 / 15

FIG. 4





FIG. 5

Polymer	Mn (VPO)	Mw/Mn (GPC)	Elemental Analysis; Found (Theory)		
			C (%)	H (%)	P (%)
P(BHET- EOP/TC, 80/20)	7918	6119 /2219	49.61 (51.82)	4.95 (4.81)	6.24 (7.03)
P(BHET- HOP/TC, 90/10)	6364	4201 /1587	51.67 (53.11)	5.99 (5.90)	6.26 (6.77)

5 / 15

FIG. 6



6 / 15

FIG. 7A






FIG. 7B



7 / 15


FIG. 8



- p(BHDPT-EOP)
- p(BHDPT-EOP/TC, 85/15)
- ▲— p(BHDPT-EOP/TC, 75/25)
- ◆— p(BHDPT-EOP/TC, 50/50)

8 / 15

FIG. 9



P(BHET-EOP/TC, 80/20) Microspheres  
Containing FITC-BSA





FIG.10




10 / 15

FIG. 11




11 / 15

FIG. 12



12 / 15

FIG. 13



13 / 15

FIG. 14




FIG. 15





FIG. 16



# INTERNATIONAL SEARCH REPORT

II. International Application No  
PCT/US 98/06381

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C08G63/692 A61L17/00 A61L25/00 A61L27/00 A61K9/16

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C08G A61L A61K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 057 116 A (LORCA MARIN S.A.) 4 August 1982  see claims 1-6,8,9	1-4, 8-19, 23-29, 51,52
A	CHEMICAL ABSTRACTS, vol. 99, no. 22, 28 November 1983 Columbus, Ohio, US; abstract no. 176481, AKUTIN ET AL.: "Polyarylates" XP002070262 see abstract & SU 203 231 A	1,2,8,9, 11-14, 17,23, 32,38
A	US 4 474 937 A (BALES) 2 October 1984 see claims 1-5	1

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

### \* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

3 July 1998

Date of mailing of the international search report

21/07/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nt,  
Fax: (+31-70) 340-3016

Authorized officer

Decocker, L

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 98/06381

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 57116	A	04-08-1982	FR 2498612 A	30-07-1982
US 4474937	A	02-10-1984	AU 569325 B	28-01-1988
			AU 3338884 A	18-04-1985
			CA 1217897 A	07-02-1987
			EP 0138099 A	24-04-1985
			JP 60096619 A	30-05-1985